





2012 *Bay Star*

12B915 CAFÉ LATTÉ

- SKIN: 60452 COGNAC BROWN MICA
- A - 62447 CHESTNUT PEARL
- B - 64548 NEWMAR SOVEREIGN
- C - 44429 ANTELOPE MET.

AWNING:
STD: A&E DOMETIC 9000 SERIES
FABRIC: LINEN TWEED
HARDWARE: BLACK

Paint Code Formulas - BASF *Diamont*

2012 BAY STAR 12B915 - CAFÉ LATE

SKIN: 60452	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			<i>Grams</i>	<i>Cum.</i>	<i>Grams</i>	<i>Cum. Grams</i>
COGNAC BROWN MICA, COGNAC BROWN MICA MET	UR50	UNIVERSAL MID TEMP REDUCER	79.58	79.58	318.3	318.3
	BC101	FLOP CONTROL	10.50	90.08	42.0	360.3
	BC171	MEDIUM ALUMINUM	77.80	167.88	311.2	671.5
	BC200	BLACK	372.35	540.23	1489.4	2160.9
	BC605	YELLOW OXIDE	8.75	548.98	35.0	2195.9
	BC800	RED GOLD	18.35	567.33	73.4	2269.3
	CB74L	BRIGHT COPPER PEARL	69.90	637.23	279.6	2548.9
	BC100	CLEAR	236.85	874.08	947.4	3496.3
COLOR A: 62447	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			<i>Grams</i>	<i>Cum.</i>	<i>Grams</i>	<i>Cum. Grams</i>
BROWN MICA, BROWN MICA MET	UR50	UNIVERSAL MID TEMP REDUCER	72.50	72.50	290.0	290.0
	BC101	FLOP CONTROL	48.33	120.83	193.3	483.3
	BC171	MEDIUM ALUMINUM	243.10	363.93	972.4	1455.7
	BC175	MEDIUM STARFLAKE ALUMINUM	32.63	396.55	130.5	1586.2
	BC200	BLACK	399.20	795.75	1596.8	3183.0
	BC800	RED GOLD	35.28	831.03	141.1	3324.1
	BC821	DARK MAROON	27.80	858.83	111.2	3435.3
	BC610	GREEN GOLD	10.88	869.70	43.5	3478.8
COLOR B: 64548	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			<i>Grams</i>	<i>Cum.</i>	<i>Grams</i>	<i>Cum. Grams</i>
SOVEREIGN MET, SOVEREIGN	UR50	UNIVERSAL MID TEMP REDUCER	82.83	82.83	331.3	331.3
	BC140	MEDIUM FINE IRIDESCENT	291.73	374.55	1166.9	1498.2
	BC170	MEDIUM IRIDESCENT	204.88	579.43	819.5	2317.7
	BC621	YELLOW GOLD	146.05	725.48	584.2	2901.9
	BC600	GOLD	85.63	811.10	342.5	3244.4
	BC840	RED VIOLET	21.20	832.30	84.8	3329.2
	BC200	BLACK	20.40	852.70	81.6	3410.8
	BC805	RED OXIDE	13.63	866.33	54.5	3465.3
COLOR C: 44429 (44429A)	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			<i>Grams</i>	<i>Cum.</i>	<i>Grams</i>	<i>Cum. Grams</i>
LIGHT CHAMPAGNE MET	UR50	UNIVERSAL MID TEMP REDUCER	83.00	83.00	332.0	332.0
	BC101	FLOP CONTROL	103.00	186.00	412.0	744.0
	BC171	MEDIUM ALUMINUM	402.40	588.40	1609.6	2353.6
	BC170	MEDIUM IRIDESCENT	172.40	760.80	689.6	3043.2
	BC190	WHITE	18.80	779.60	75.2	3118.4
	BC250	BLUE BLACK	46.20	825.80	184.8	3303.2
	BC800	RED GOLD	43.20	869.00	172.8	3476.0
	BC821	DARK MAROON	6.00	875.00	24.0	3500.0

Paint Code Formulas - BASF Onyx Waterborne

2012 BAY STAR 12B915 - CAFÉ LATE

SKIN: 60452 COGNAC BROWN MICA, COGNAC BROWN MICA MET	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
	HB002	HYDRO BASE	635.78	635.78	2543.1	2543.1
	HB203	DEEP BLACK	145.55	781.33	582.2	3125.3
	CB74L	BRIGHT COPPER PEARL	103.95	885.28	415.8	3541.1
	HB120	FINE ALUMINUM	24.05	909.33	96.2	3637.3
	HB200	BLUE BLACK	20.75	930.08	83.0	3720.3
	HB670	YELLOW OXIDE	13.07	943.15	52.3	3772.6
	HB090	FLOP CONTROL	25.20	968.35	100.8	3873.4
COLOR A: 62447 BROWN MICA, BROWN MICA MET	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
	HB002	HYDRO BASE	614.10	614.10	2456.4	2456.4
	HB203	DEEP BLACK	117.85	731.95	471.4	2927.8
	HB150	MEDIUM ALUMINUM	69.75	801.70	279.0	3206.8
	HB110	ULTRA FINE ALUMINUM	26.40	828.10	105.6	3312.4
	HB780	RED GOLD	21.65	849.75	86.6	3399.0
	HB880	RED VIOLET	13.25	863.00	53.0	3452.0
	HB861	MAROON	10.85	873.85	43.4	3495.4
	HB090	FLOP CONTROL	80.53	954.38	322.1	3817.5
COLOR B: 64548 SOVEREIGN MET, SOVEREIGN	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
	HB002	HYDRO BASE	609.63	609.63	2438.5	2438.5
	HB680	GOLD	133.28	742.90	533.1	2971.6
	HB650	YELLOW GOLD	67.18	810.08	268.7	3240.3
	HB130	FINE ALUMINUM	60.63	870.70	242.5	3482.8
	HB110	ULTRA FINE ALUMINUM	50.88	921.58	203.5	3686.3
	HB150	MEDIUM ALUMINUM	25.95	947.53	103.8	3790.1
	HB870	MAGENTA	15.18	962.70	60.7	3850.8
	HB740	BRIGHT ORANGE	5.45	968.15	21.8	3872.6
	HB203	DEEP BLACK	5.45	973.60	21.8	3894.4
COLOR C: 44429 (44429A) LIGHT CHAMPAGNE MET	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
	HB002	HYDRO BASE	598.90	598.90	2395.6	2395.6
	HB130	FINE ALUMINUM	120.23	719.13	480.9	2876.5
	HB150	MEDIUM ALUMINUM	86.10	805.23	344.4	3220.9
	HB999	LOW STRENGTH WHITE	66.23	871.45	264.9	3485.8
	HB780	RED GOLD	29.78	901.23	119.1	3604.9
	HB200	BLUE BLACK	19.85	921.08	79.4	3684.3
	HB861	MAROON	6.67	927.75	26.7	3711.0
	HB090	FLOP CONTROL	47.45	975.20	189.8	3900.8