






2013
Essex

13B180 - FLEMING

- SKIN: 64443 PEARL BLACK MET.
- A - 58829A NEW SILVER
- B - 49557 GRANITE MET.
- C - 60990A BIARRITZ WHITE MET.
- D - 64047 THUNDER GREY MET.

AWNING: GIRARD
FABRIC: CHARCOAL TWEED (SUNBRELLA)
HARDWARE: BLACK

2013 ESSEX 13B180 - FLEMING

SKIN:		BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
PEARL BLACK, BLACK PEARL MET		UR50	UNIVERSAL MID TEMP REDUCER	80.38	80.38	321.5	321.5
		BC105	WHITE	7.30	87.68	29.2	350.7
		BC118	BLUE PEARL	32.48	120.15	129.9	480.6
		BC1190	CRYSTAL WHITE	36.13	156.28	144.5	625.1
		BC171	MEDIUM ALUMINUM	4.88	161.15	19.5	644.6
		BC200	BLACK	675.10	836.25	2700.4	3345.0
		BC410	GREEN BLUE	11.78	848.03	47.1	3392.1
		BC805	RED OXIDE	12.58	860.60	50.3	3442.4
		BC101	FLOP CONTROL	8.93	869.53	35.7	3478.1
COLOR A: 58829 (58829A)							
SILVER, NEWMAR SILVER		BC140	MEDIUM FINE IRIDESCENT	790.28	790.28	3161.1	3161.1
		BC101	FLOP CONTROL	74.80	865.08	299.2	3460.3
COLOR B: 49557							
GRANITE MET		UR50	UNIVERSAL MID TEMP REDUCER	78.65	78.65	314.6	314.6
		BC105	WHITE	58.38	137.03	233.5	548.1
		BC171	MEDIUM ALUMINUM	108.43	245.45	433.7	981.8
		BC180	COARSE IRIDESCENT	103.28	348.73	413.1	1394.9
		BC200	BLACK	167.20	515.93	668.8	2063.7
		BC250	BLUE BLACK	248.63	764.55	994.5	3058.2
		BC300	CARBAZOLE VIOLET	37.73	802.28	150.9	3209.1
		BC410	GREEN BLUE	42.90	845.18	171.6	3380.7
		BC101	FLOP CONTROL	25.83	871.00	103.3	3484.0
COLOR C: 60990 (60990A)							
BIARRITZ WHITE, BIARRITZ WHITE MET		UR50	UNIVERSAL MID TEMP REDUCER	84.15	84.15	336.6	336.6
		D902	HI HIDING WHITE	938.30	1022.45	3753.2	4089.8
		BC209	BLACK TONER	28.60	1051.05	114.4	4204.2
		BC605	YELLOW OXIDE	13.58	1064.63	54.3	4258.5

PAINT CODE FORMULAS - BASF DIAMONT

2013 ESSEX 13B180 - FLEMING

COLOR D: 64047

THUNDER GREY MET

BASE #	BASE NAME	1 QT <i>Grams</i>	1 QUART <i>Cum.</i>	1 GLN <i>Grams</i>	1 GALLON <i>Cum. Grams</i>
UR50	UNIVERSAL MID TEMP REDUCER	79.50	79.50	318.0	318.0
BC101	FLOP CONTROL	37.55	117.05	150.2	468.2
BC110	WHITE PEARL	199.18	316.23	796.7	1264.9
BC200	BLACK	347.70	663.93	1390.8	2655.7
BC250	BLUE BLACK	106.58	770.50	426.3	3082.0
BC300	CARBAZOLE VIOLET	34.10	804.60	136.4	3218.4
BC470	VIOLET BLUE	62.00	866.60	248.0	3466.4
BC800	RED GOLD	6.98	873.58	27.9	3494.3

PAINT CODE FORMULAS - BASF ONYX WATERBORNE

2013 ESSEX 13B180 - FLEMING

SKIN: 64443	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
	HB002	HYDRO BASE	665.58	665.58	2662.3	2662.3
	HB203	DEEP BLACK	211.58	877.15	846.3	3508.6
	HB46L	BLUE PEARL	31.33	908.48	125.3	3633.9
	HB99L	CRYSTAL WHITE	19.55	928.03	78.2	3712.1
	HB670	YELLOW OXIDE	13.65	941.68	54.6	3766.7
	HB999	LOW STRENGTH WHITE	3.93	945.60	15.7	3782.4
	HB150	MEDIUM ALUMINUM	2.95	948.55	11.8	3794.2
	HB090	FLOP CONTROL	8.85	957.40	35.4	3829.6
COLOR A: 58829 (58829A)	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
	HB002	HYDRO BASE	648.50	648.50	2594.0	2594.0
	HB110	ULTRA FINE ALUMINUM	193.50	842.00	774.0	3368.0
	HB130	FINE ALUMINUM	31.88	873.88	127.5	3495.5
	HB090	FLOP CONTROL	79.73	953.60	318.9	3814.4
COLOR B: 49557	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
	HB002	HYDRO BASE	576.88	576.88	2307.5	2307.5
	HB200	BLUE BLACK	226.88	803.75	907.5	3215.0
	HB140	MEDIUM ALUMINUM	40.00	843.75	160.0	3375.0
	HB150	MEDIUM ALUMINUM	38.93	882.68	155.7	3530.7
	HB460	GREEN BLUE	38.85	921.53	155.4	3686.1
	HB203	DEEP BLACK	33.53	955.05	134.1	3820.2
	HB300	CARBAZOLE VIOLET	17.28	972.33	69.1	3889.3
COLOR C: 60990 (60990A)	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
	HB002	HYDRO BASE	492.78	492.78	1971.1	1971.1
	HB990	WHITE	673.38	1166.15	2693.5	4664.6
	HB259	LOW STRENGTH BLACK	13.27	1179.43	53.1	4717.7
	HB409	PHTHALO BLUE	12.08	1191.50	48.3	4766.0
	HB670	YELLOW OXIDE	3.63	1195.13	14.5	4780.5
	HB779	RED OXIDE	2.42	1197.55	9.7	4790.2

PAINT CODE FORMULAS - BASF ONYX WATERBORNE

2013 ESSEX 13B180 - FLEMING

COLOR D: 64047

THUNDER GREY MET

[illegible]