



2014
Bay Star

14B420 HAZELNUT

- SKIN: 62922A GALAXY GOLD MET.
- A - 574482 ROSSO BORDEAU
- B - 64443 PEARL BLACK MET.
- C - 62447 NEWMAR BROWN MICA

AWNING:
 STD: A&E DOMETIC 9000 SERIES
 FABRIC: WALNUT BROWN TWEED
 HARDWARE: BLACK

Paint Code Formulas - BASF *Diamont*

2014 BAY STAR 14B420 - HAZELNUT

SKIN: 62922 (62922A)	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON	
			<i>Grams</i>	<i>Cum.</i>	<i>Grams</i>	<i>Cum. Grams</i>	
	GALAXY GOLD MET	UR50	UNIVERSAL MID TEMP REDUCER	88.65	88.65	354.6	354.6
		BC101	FLOP CONTROL	23.43	112.08	93.7	448.3
		BC171	MEDIUM ALUMINUM	499.93	612.00	1999.7	2448.0
		BC209	BLACK TONER	8.88	620.88	35.5	2483.5
		BC605	YELLOW OXIDE	44.08	664.95	176.3	2659.8
		BC655	ORGANIC YELLOW	21.63	686.58	86.5	2746.3
		BC805	RED OXIDE	45.93	732.50	183.7	2930.0
		CB85L	RED PEARL	69.30	801.80	277.2	3207.2
BC100		CLEAR	87.35	889.15	349.4	3556.6	
COLOR A: 574482	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON	
			<i>Grams</i>	<i>Cum.</i>	<i>Grams</i>	<i>Cum. Grams</i>	
	ROSSO BORDEAU	UR50	UNIVERSAL MID TEMP REDUCER	79.53	79.53	318.1	318.1
		BC140	MEDIUM FINE IRIDESCENT	9.58	89.10	38.3	356.4
		BC170	MEDIUM IRIDESCENT	14.33	103.43	57.3	413.7
		BC300	CARBAZOLE VIOLET	104.13	207.55	416.5	830.2
		BC116	SUPER RUSSET PEARL	38.13	245.68	152.5	982.7
		BC200	BLACK	41.38	287.05	165.5	1148.2
		BC805	RED OXIDE	58.88	345.93	235.5	1383.7
		BC821	DARK MAROON	528.65	874.58	2114.6	3498.3
COLOR B: 64443	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON	
			<i>Grams</i>	<i>Cum.</i>	<i>Grams</i>	<i>Cum. Grams</i>	
	PEARL BLACK, BLACK PEARL MET	UR50	UNIVERSAL MID TEMP REDUCER	80.35	80.35	321.4	321.4
		BC105	WHITE	7.30	87.65	29.2	350.6
		BC118	BLUE PEARL	32.48	120.13	129.9	480.5
		BC1190	CRYSTAL WHITE	36.13	156.25	144.5	625.0
		BC171	MEDIUM ALUMINUM	4.88	161.13	19.5	644.5
		BC200	BLACK	674.85	835.98	2699.4	3343.9
		BC410	GREEN BLUE	11.78	847.75	47.1	3391.0
		BC805	RED OXIDE	12.58	860.33	50.3	3441.3
BC101		FLOP CONTROL	8.93	869.25	35.7	3477.0	
COLOR C: 62447	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON	
			<i>Grams</i>	<i>Cum.</i>	<i>Grams</i>	<i>Cum. Grams</i>	
	BROWN MICA, BROWN MICA MET	UR50	UNIVERSAL MID TEMP REDUCER	72.48	72.48	289.9	289.9
		BC101	FLOP CONTROL	48.30	120.78	193.2	483.1
		BC171	MEDIUM ALUMINUM	243.00	363.78	972.0	1455.1
		BC175	MEDIUM STARFLAKE ALUMINUM	32.60	396.38	130.4	1585.5
		BC200	BLACK	399.03	795.40	1596.1	3181.6
		BC800	RED GOLD	35.28	830.68	141.1	3322.7
		BC821	DARK MAROON	27.78	858.45	111.1	3433.8
		BC610	GREEN GOLD	10.88	869.33	43.5	3477.3

Paint Code Formulas - BASF Onyx Waterborne

2014 BAY STAR 14B420 - HAZELNUT

SKIN: 62922 (62922A)	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
GALAXY GOLD MET	HB002	HYDRO BASE	631.38	631.38	2525.5	2525.5
	HB120	FINE ALUMINUM	146.75	778.13	587.0	3112.5
	CB85L	RED PEARL	107.60	885.73	430.4	3542.9
	HB670	YELLOW OXIDE	31.53	917.25	126.1	3669.0
	HB617	ORGANIC YELLOW	20.73	937.98	82.9	3751.9
	HB770	RED OXIDE	13.07	951.05	52.3	3804.2
	HB259	LOW STRENGTH BLACK	13.00	964.05	52.0	3856.2
	HB740	BRIGHT ORANGE	5.45	969.50	21.8	3878.0
	HB090	FLOP CONTROL	29.33	998.83	117.3	3995.3
COLOR A: 574482	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
ROSSO BORDEAU	HB002 Step 1	HYDRO BASE	537.30	537.30	2149.2	2149.2
	HB990 Step 1	WHITE	565.23	1102.53	2260.9	4410.1
	HB250 Step 1	BLACK	53.63	1156.15	214.5	4624.6
	HB002 Step 2	HYDRO BASE	622.75	1778.90	2491.0	7115.6
	HB861 Step 2	MAROON	208.83	1987.73	835.3	7950.9
	HB300 Step 2	CARBAZOLE VIOLET	46.35	2034.08	185.4	8136.3
	HB88L Step 2	RUSSET PEARL	29.93	2064.00	119.7	8256.0
	HB740 Step 2	BRIGHT ORANGE	18.38	2082.38	73.5	8329.5
	HB200 Step 2	BLUE BLACK	13.55	2095.93	54.2	8383.7
	HB961 Step 2	TRANSPARENT WHITE	7.68	2103.60	30.7	8414.4
	HB130 Step 2	FINE ALUMINUM	1.92	2105.53	7.7	8422.1
	HB090 Step 2	FLOP CONTROL	4.80	2110.33	19.2	8441.3
COLOR B: 64443	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
PEARL BLACK, BLACK PEARL MET	HB002	HYDRO BASE	665.58	665.58	2662.3	2662.3
	HB203	DEEP BLACK	211.58	877.15	846.3	3508.6
	HB46L	BLUE PEARL	31.33	908.48	125.3	3633.9
	HB99L	CRYSTAL WHITE	19.55	928.03	78.2	3712.1
	HB670	YELLOW OXIDE	13.65	941.68	54.6	3766.7
	HB999	LOW STRENGTH WHITE	3.93	945.60	15.7	3782.4
	HB150	MEDIUM ALUMINUM	2.95	948.55	11.8	3794.2
	HB090	FLOP CONTROL	8.85	957.40	35.4	3829.6
COLOR C: 62447	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
BROWN MICA, BROWN MICA MET	HB002	HYDRO BASE	614.10	614.10	2456.4	2456.4
	HB203	DEEP BLACK	117.85	731.95	471.4	2927.8
	HB150	MEDIUM ALUMINUM	69.75	801.70	279.0	3206.8
	HB110	ULTRA FINE ALUMINUM	26.40	828.10	105.6	3312.4
	HB780	RED GOLD	21.65	849.75	86.6	3399.0
	HB880	RED VIOLET	13.25	863.00	53.0	3452.0
	HB861	MAROON	10.85	873.85	43.4	3495.4
	HB090	FLOP CONTROL	80.53	954.38	322.1	3817.5