





2015 *Bay Star*

- SKIN: 64546C PEPPER WHITE
- A - 574482 ROSSO BORDEAU
- B - 595303 LIGHT GOLD MET.
- C - 64443 PEARL BLACK MET.

UNIT: 111742

DEALER: Mount Comfort RV

SPECIAL: 1503

**PLEASE ACKNOWLEDGE AND DATE THE FOLLOWING
ORDER/PRINT FOR APPROVAL TO BUILD, AND FAX TO
NEWMAR (AT 574-773-2895) AS SOON AS POSSIBLE**

DATE: _____

SIGN: _____

Paint Code Formulas - BASF *Diamont*

SPECIAL FOR UNIT # 111742 - 2015 BAY STAR

SKIN: 64546 (64546C)	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			Grams	Cum.	Grams	Cum. Grams
PEPPER WHITE	UR50	UNIVERSAL MID TEMP REDUCER	78.93	78.93	315.7	315.7
	BC101	FLOP CONTROL	86.68	165.60	346.7	662.4
	BC191	0	724.35	889.95	2897.4	3559.8
	BC209	BLACK TONER	41.65	931.60	166.6	3726.4
	BC605	YELLOW OXIDE	22.55	954.15	90.2	3816.6
COLOR A: 574482	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			Grams	Cum.	Grams	Cum. Grams
ROSSO BORDEAU	UR50	UNIVERSAL MID TEMP REDUCER	79.53	79.53	318.1	318.1
	BC140	MEDIUM FINE IRIDESCENT	9.58	89.10	38.3	356.4
	BC170	MEDIUM IRIDESCENT	14.33	103.43	57.3	413.7
	BC300	CARBAZOLE VIOLET	104.13	207.55	416.5	830.2
	BC116	SUPER RUSSET PEARL	38.13	245.68	152.5	982.7
	BC200	BLACK	41.38	287.05	165.5	1148.2
	BC805	RED OXIDE	58.88	345.93	235.5	1383.7
	BC821	DARK MAROON	528.65	874.58	2114.6	3498.3
COLOR B: 595303	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			Grams	Cum.	Grams	Cum. Grams
LT GOLD MET, LT GOLD	UR50	UNIVERSAL MID TEMP REDUCER	80.30	80.30	321.2	321.2
	BC180	COARSE IRIDESCENT	70.63	150.93	282.5	603.7
	BC101	FLOP CONTROL	98.88	249.80	395.5	999.2
	BC821	DARK MAROON	9.73	259.53	38.9	1038.1
	BC171	MEDIUM ALUMINUM	184.43	443.95	737.7	1775.8
	BC600	GOLD	194.15	638.10	776.6	2552.4
	BC105	WHITE	36.23	674.33	144.9	2697.3
	CB66V	GOLD ALUMINUM	36.18	710.50	144.7	2842.0
	BC200	BLACK	64.45	774.95	257.8	3099.8
	BC100	CLEAR	107.65	882.60	430.6	3530.4
COLOR C: 64443	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			Grams	Cum.	Grams	Cum. Grams
PEARL BLACK, BLACK PEARL MET	UR50	UNIVERSAL MID TEMP REDUCER	80.35	80.35	321.4	321.4
	BC105	WHITE	7.30	87.65	29.2	350.6
	BC118	BLUE PEARL	32.48	120.13	129.9	480.5
	BC1190	CRYSTAL WHITE	36.13	156.25	144.5	625.0
	BC171	MEDIUM ALUMINUM	4.88	161.13	19.5	644.5
	BC200	BLACK	674.85	835.98	2699.4	3343.9
	BC410	GREEN BLUE	11.78	847.75	47.1	3391.0
	BC805	RED OXIDE	12.58	860.33	50.3	3441.3
	BC101	FLOP CONTROL	8.93	869.25	35.7	3477.0

Paint Code Formulas - BASF Onyx Waterborne

SPECIAL FOR UNIT # 111742 - 2015 BAY STAR

SKIN: 64546 (64546C)	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			Grams	Cum.	Grams	Cum. Grams
PEPPER WHITE	HB002	HYDRO BASE	495.08	495.08	1980.3	1980.3
	HB990	WHITE	590.40	1085.48	2361.6	4341.9
	HB259	LOW STRENGTH BLACK	67.05	1152.53	268.2	4610.1
	HB670	YELLOW OXIDE	15.65	1168.18	62.6	4672.7
COLOR A: 574482	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			Grams	Cum.	Grams	Cum. Grams
ROSSO BORDEAU	HB002 Step 1	HYDRO BASE	537.30	537.30	2149.2	2149.2
	HB990 Step 1	WHITE	565.23	1102.53	2260.9	4410.1
	HB250 Step 1	BLACK	53.63	1156.15	214.5	4624.6
	HB002 Step 2	HYDRO BASE	622.75	1778.90	2491.0	7115.6
	HB861 Step 2	MAROON	208.83	1987.73	835.3	7950.9
	HB300 Step 2	CARBAZOLE VIOLET	46.35	2034.08	185.4	8136.3
	HB88L Step 2	RUSSET PEARL	29.93	2064.00	119.7	8256.0
	HB740 Step 2	BRIGHT ORANGE	18.38	2082.38	73.5	8329.5
	HB200 Step 2	BLUE BLACK	13.55	2095.93	54.2	8383.7
	HB961 Step 2	TRANSPARENT WHITE	7.68	2103.60	30.7	8414.4
	HB130 Step 2	FINE ALUMINUM	1.92	2105.53	7.7	8422.1
	HB090 Step 2	FLOP CONTROL	4.80	2110.33	19.2	8441.3
COLOR B: 595303	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			Grams	Cum.	Grams	Cum. Grams
LIGHT GOLD MET, LT GOLD	HB002	HYDRO BASE	571.28	571.28	2285.1	2285.1
	HB680	GOLD	121.73	693.00	486.9	2772.0
	HB120	FINE ALUMINUM	52.05	745.05	208.2	2980.2
	CB66V	GOLD ALUMINUM	50.95	796.00	203.8	3184.0
	HB203	DEEP BLACK	26.60	822.60	106.4	3290.4
	HB999	LOW STRENGTH WHITE	25.45	848.05	101.8	3392.2
	HB140	MEDIUM ALUMINUM	25.43	873.48	101.7	3493.9
	HB861	MAROON	8.90	882.38	35.6	3529.5
	HB090	FLOP CONTROL	87.45	969.83	349.8	3879.3
COLOR C: 64443	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			Grams	Cum.	Grams	Cum. Grams
PEARL BLACK, BLACK PEARL MET	HB002	HYDRO BASE	665.58	665.58	2662.3	2662.3
	HB203	DEEP BLACK	211.58	877.15	846.3	3508.6
	HB46L	BLUE PEARL	31.33	908.48	125.3	3633.9
	HB99L	CRYSTAL WHITE	19.55	928.03	78.2	3712.1
	HB670	YELLOW OXIDE	13.65	941.68	54.6	3766.7
	HB999	LOW STRENGTH WHITE	3.93	945.60	15.7	3782.4
	HB150	MEDIUM ALUMINUM	2.95	948.55	11.8	3794.2
	HB090	FLOP CONTROL	8.85	957.40	35.4	3829.6