



# 2015 LONDON AIRE

- SKIN: 64147 SALSA RED PEARL
- A - 60990A BIARRITZ WHITE MET.
- B - 64443 PEARL BLACK MET.
- C - 63227 NEWMAR ANTHRACITE MET.

UNIT: 501202  
 DEALER: SOUTHAVEN RV  
 SPECIAL: 1020

PLEASE ACKNOWLEDGE AND DATE THE FOLLOWING  
 ORDER/PRINT FOR APPROVAL TO BUILD, AND FAX TO  
 NEWMAR (AT 574-773-2895) AS SOON AS POSSIBLE

DATE: \_\_\_\_\_

SIGN: \_\_\_\_\_

# Paint Code Formulas - BASF *Diamont*

SPECIAL FOR UNIT # 501202 - 2015 LONDON AIRE

SKIN: 64147	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
SALSA RED PEARL, SALSA RED PEARL MET	UR50	UNIVERSAL MID TEMP REDUCER	80.73	80.73	322.9	322.9
	BC101	FLOP CONTROL	49.55	130.28	198.2	521.1
	BC105	WHITE	44.38	174.65	177.5	698.6
	BC116	SUPER RUSSET PEARL	212.63	387.28	850.5	1549.1
	BC200	BLACK	46.78	434.05	187.1	1736.2
	BC805	RED OXIDE	41.58	475.63	166.3	1902.5
	BC821	DARK MAROON	410.08	885.70	1640.3	3542.8
COLOR A: 60990 (60990A)	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
BIARRITZ WHITE, BIARRITZ WHITE MET	UR50	UNIVERSAL MID TEMP REDUCER	84.10	84.10	336.4	336.4
	D902	HI HIDING WHITE	937.73	1021.83	3750.9	4087.3
	BC209	BLACK TONER	28.60	1050.43	114.4	4201.7
	BC605	YELLOW OXIDE	13.55	1063.98	54.2	4255.9
COLOR B: 64443	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
PEARL BLACK, BLACK PEARL MET	UR50	UNIVERSAL MID TEMP REDUCER	80.35	80.35	321.4	321.4
	BC105	WHITE	7.30	87.65	29.2	350.6
	BC118	BLUE PEARL	32.48	120.13	129.9	480.5
	BC1190	CRYSTAL WHITE	36.13	156.25	144.5	625.0
	BC171	MEDIUM ALUMINUM	4.88	161.13	19.5	644.5
	BC200	BLACK	674.85	835.98	2699.4	3343.9
	BC410	GREEN BLUE	11.78	847.75	47.1	3391.0
	BC805	RED OXIDE	12.58	860.33	50.3	3441.3
	BC101	FLOP CONTROL	8.93	869.25	35.7	3477.0
COLOR C: 63227	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
ANTHRACITE MET, NEWMAR ANTHRACITE MET	UR50	UNIVERSAL MID TEMP REDUCER	80.08	80.08	320.3	320.3
	BC171	MEDIUM ALUMINUM	35.23	115.30	140.9	461.2
	BC185	COARSE STARFLAKE ALUMINUM	288.23	403.53	1152.9	1614.1
	BC195	TRANSPARENT WHITE	6.00	409.53	24.0	1638.1
	BC200	BLACK	273.03	682.55	1092.1	2730.2
	BC250	BLUE BLACK	100.88	783.43	403.5	3133.7
	BC300	CARBAZOLE VIOLET	15.63	799.05	62.5	3196.2
	BC406	PHHALO BLUE	30.03	829.08	120.1	3316.3
	CB44L	BRIGHT BLUE	8.80	837.88	35.2	3351.5
	BC101	FLOP CONTROL	40.43	878.30	161.7	3513.2

# Paint Code Formulas - BASF Onyx Waterborne

SPECIAL FOR UNIT # 501202 - 2015 LONDON AIRE

SKIN: 64147	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
SALSA RED PEARL, SALSA RED PEARL MET	HB002 Step 1	HYDRO BASE	577.65	577.65	2310.6	2310.6
	HB990 Step 1	WHITE	423.13	1000.78	1692.5	4003.1
	HB250 Step 1	BLACK	101.73	1102.50	406.9	4410.0
	HB002 Step 2	HYDRO BASE	588.85	1691.35	2355.4	6765.4
	HB861 Step 2	MAROON	131.95	1823.30	527.8	7293.2
	HB88M Step 2	SUPER RUSSET PEARL	51.35	1874.65	205.4	7498.6
	HB870 Step 2	MAGENTA	35.65	1910.30	142.6	7641.2
	HB88L Step 2	RUSSET PEARL	23.08	1933.38	92.3	7733.5
	HB250 Step 2	BLACK	17.78	1951.15	71.1	7804.6
	HB999 Step 2	LOW STRENGTH WHITE	8.38	1959.53	33.5	7838.1
	HB090 Step 2	FLOP CONTROL	93.23	2052.75	372.9	8211.0
COLOR A: 60990 (60990A)	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
BIARRITZ WHITE, BIARRITZ WHITE MET	HB002	HYDRO BASE	492.78	492.78	1971.1	1971.1
	HB990	WHITE	673.38	1166.15	2693.5	4664.6
	HB259	LOW STRENGTH BLACK	13.27	1179.43	53.1	4717.7
	HB409	PHTHALO BLUE	12.08	1191.50	48.3	4766.0
	HB670	YELLOW OXIDE	3.63	1195.13	14.5	4780.5
	HB779	RED OXIDE	2.42	1197.55	9.7	4790.2
COLOR B: 64443	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
PEARL BLACK, BLACK PEARL MET	HB002	HYDRO BASE	665.58	665.58	2662.3	2662.3
	HB203	DEEP BLACK	211.58	877.15	846.3	3508.6
	HB46L	BLUE PEARL	31.33	908.48	125.3	3633.9
	HB99L	CRYSTAL WHITE	19.55	928.03	78.2	3712.1
	HB670	YELLOW OXIDE	13.65	941.68	54.6	3766.7
	HB999	LOW STRENGTH WHITE	3.93	945.60	15.7	3782.4
	HB150	MEDIUM ALUMINUM	2.95	948.55	11.8	3794.2
	HB090	FLOP CONTROL	8.85	957.40	35.4	3829.6
COLOR C: 63227	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
ANTHRACITE MET, NEWMAR ANTHRACITE MET	HB002	HYDRO BASE	626.60	626.60	2506.4	2506.4
	HB250	BLACK	132.88	759.48	531.5	3037.9
	HB200	BLUE BLACK	48.45	807.93	193.8	3231.7
	HB175	MEDIUM STARFLAKE ALUMINUM	39.10	847.03	156.4	3388.1
	HB444	BLUE	15.40	862.43	61.6	3449.7
	HB619	LIGHT YELLOW	13.38	875.80	53.5	3503.2
	HB46L	BLUE PEARL	8.23	884.03	32.9	3536.1
	CB34M	VIOLET PEARL	2.00	886.03	8.0	3544.1
	HB471	PHTHALO BLUE	2.08	888.10	8.3	3552.4
	HB090	FLOP CONTROL	62.85	950.95	251.4	3803.8