





2015

KING AIRE

- SKIN: 56680 CAJUN SPICE OBSIDIAN
- A - 703A NEWMAR MOONSTONE GOLD
- B - 60452 COGNAC BROWN MICA
- C - 575874A EGGSHELL



UNIT: 530281
DEALER: TOM JOHNSON
SPECIAL: 548

PLEASE ACKNOWLEDGE AND DATE THE FOLLOWING
ORDER/PRINT FOR APPROVAL TO BUILD, AND FAX TO
NEWMAR (AT 574-773-2895) AS SOON AS POSSIBLE

DATE: _____

SIGN: _____

Paint Code Formulas - BASF *Diamont*

SPECIAL FOR UNIT # 530281 - 2015 KING AIRE

SKIN: 56680	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			Grams	Cum.	Grams	Cum. Grams
CAJON SPICE OBSIDIAN PEARL, OBSIDIAN BLACK MET	UR50	UNIVERSAL MID TEMP REDUCER	95.90	95.90	383.6	383.6
	BC194	HI HIDING WHITE	907.35	1003.25	3629.4	4013.0
	BC250	BLUE BLACK	4.23	1007.48	16.9	4029.9
	BC605	YELLOW OXIDE	24.25	1031.73	97.0	4126.9
	BC809		22.13	1053.85	88.5	4215.4
COLOR A: 703 (703A)	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			Grams	Cum.	Grams	Cum. Grams
MOONSTONE GOLD, MOONSTONE MET	UR50	UNIVERSAL MID TEMP REDUCER	77.50	77.50	310.0	310.0
	BC175	MEDIUM STARFLAKE ALUMINUM	247.20	324.70	988.8	1298.8
	BC140	MEDIUM FINE IRIDESCENT	244.65	569.35	978.6	2277.4
	BC800	RED GOLD	123.18	692.53	492.7	2770.1
	BC201	DEEP BLACK	117.18	809.70	468.7	3238.8
	BC105	WHITE	44.75	854.45	179.0	3417.8
	BC101	FLOP CONTROL	18.10	872.55	72.4	3490.2
	CB74L	BRIGHT COPPER PEARL	5.15	877.70	20.6	3510.8
	BC615	LIGHT YELLOW	3.48	881.18	13.9	3524.7
COLOR B: 60452	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			Grams	Cum.	Grams	Cum. Grams
COGNAC BROWN MICA, COGNAC BROWN MICA MET	UR50	UNIVERSAL MID TEMP REDUCER	79.50	79.50	318.0	318.0
	BC101	FLOP CONTROL	10.48	89.98	41.9	359.9
	BC171	MEDIUM ALUMINUM	77.70	167.68	310.8	670.7
	BC200	BLACK	371.95	539.63	1487.8	2158.5
	BC605	YELLOW OXIDE	8.75	548.38	35.0	2193.5
	BC800	RED GOLD	18.33	566.70	73.3	2266.8
	CB74L	BRIGHT COPPER PEARL	69.85	636.55	279.4	2546.2
	BC100	CLEAR	236.60	873.15	946.4	3492.6
COLOR C: 575874 (575874A)	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			Grams	Cum.	Grams	Cum. Grams
EGGSHELL	UR50	UNIVERSAL MID TEMP REDUCER	79.03	79.03	316.1	316.1
	BC191	0	733.45	812.48	2933.8	3249.9
	BC209	BLACK TONER	27.08	839.55	108.3	3358.2
	BC605	YELLOW OXIDE	24.55	864.10	98.2	3456.4
	BC805	RED OXIDE	4.33	868.43	17.3	3473.7
	BC101	FLOP CONTROL	87.15	955.58	348.6	3822.3

Paint Code Formulas - BASF Onyx Waterborne

SPECIAL FOR UNIT # 530281 - 2015 KING AIRE

SKIN: 56680 CAJON SPICE OBSIDIAN PEARL, OBSIDIAN BLACK MET	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
	HB002	HYDRO BASE	665.33	665.33	2661.3	2661.3
	HB203	DEEP BLACK	227.93	893.25	911.7	3573.0
	HB200	BLUE BLACK	20.25	913.50	81.0	3654.0
	HB770	RED OXIDE	11.63	925.13	46.5	3700.5
	HB670	YELLOW OXIDE	9.70	934.83	38.8	3739.3
	HB999	LOW STRENGTH WHITE	8.67	943.50	34.7	3774.0
	HB462	SAPPHIRE 2	5.85	949.35	23.4	3797.4
	HB150	MEDIUM ALUMINUM	2.00	951.35	8.0	3805.4
	HB130	FINE ALUMINUM	1.92	953.28	7.7	3813.1
COLOR A: 703 (703A) MOONSTONE GOLD, MOONSTONE MET	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
	HB002	HYDRO BASE	644.90	644.90	2579.6	2579.6
	HB110	ULTRA FINE ALUMINUM	78.90	723.80	315.6	2895.2
	HB780	RED GOLD	75.80	799.60	303.2	3198.4
	HB203	DEEP BLACK	70.65	870.25	282.6	3481.0
	HB175	MEDIUM STARFLAKE ALUMINUM	46.15	916.40	184.6	3665.6
	HB150	MEDIUM ALUMINUM	16.35	932.75	65.4	3731.0
	HB610	YELLOW	10.20	942.95	40.8	3771.8
	HB999	LOW STRENGTH WHITE	9.17	952.13	36.7	3808.5
	CB74L	BRIGHT COPPER PEARL	2.08	954.20	8.3	3816.8
COLOR B: 60452 COGNAC BROWN MICA, COGNAC BROWN MICA MET	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
	HB002	HYDRO BASE	635.78	635.78	2543.1	2543.1
	HB203	DEEP BLACK	145.55	781.33	582.2	3125.3
	CB74L	BRIGHT COPPER PEARL	103.95	885.28	415.8	3541.1
	HB120	FINE ALUMINUM	24.05	909.33	96.2	3637.3
	HB200	BLUE BLACK	20.75	930.08	83.0	3720.3
	HB670	YELLOW OXIDE	13.07	943.15	52.3	3772.6
	HB090	FLOP CONTROL	25.20	968.35	100.8	3873.4
COLOR C: 575874 (575874A) EGGSHELL	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
	HB002	HYDRO BASE	492.50	492.50	1970.0	1970.0
	HB990	WHITE	504.30	996.80	2017.2	3987.2
	HB779	RED OXIDE	65.05	1061.85	260.2	4247.4
	HB259	LOW STRENGTH BLACK	54.13	1115.98	216.5	4463.9
	HB670	YELLOW OXIDE	21.73	1137.70	86.9	4550.8