





2015 KING AIRE

- SKIN: 64443 PEARL BLACK MET.
- A - 85670A NEWMAR SLATE MET.
- B - 64147 SALSA RED PEARL
- C - 60990A BIARRITZ WHITE MET.

UNIT: 530307
DEALER: TRANSWEST TRUCK, CO.
SPECIAL: 1319

PLEASE ACKNOWLEDGE AND DATE THE FOLLOWING
ORDER/PRINT FOR APPROVAL TO BUILD, AND FAX TO
NEWMAR (AT 574-773-2895) AS SOON AS POSSIBLE

DATE: _____

SIGN: _____

SPECIAL FOR UNIT # 530307 - 2015 KING AIRE

COLOR B: 64147

Paint Code Formulas - BASF Onyx Waterborne

SPECIAL FOR UNIT # 530307 - 2015 KING AIRE

SKIN: 64443	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
	HB002	HYDRO BASE	665.58	665.58	2662.3	2662.3
	HB203	DEEP BLACK	211.58	877.15	846.3	3508.6
	HB46L	BLUE PEARL	31.33	908.48	125.3	3633.9
	HB99L	CRYSTAL WHITE	19.55	928.03	78.2	3712.1
	HB670	YELLOW OXIDE	13.65	941.68	54.6	3766.7
	HB999	LOW STRENGTH WHITE	3.93	945.60	15.7	3782.4
	HB150	MEDIUM ALUMINUM	2.95	948.55	11.8	3794.2
	HB090	FLOP CONTROL	8.85	957.40	35.4	3829.6
PEARL BLACK, BLACK PEARL MET	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
	HB002	HYDRO BASE	652.05	652.05	2608.2	2608.2
	HB203	DEEP BLACK	95.85	747.90	383.4	2991.6
	HB130	FINE ALUMINUM	76.25	824.15	305.0	3296.6
	HB140	MEDIUM ALUMINUM	55.65	879.80	222.6	3519.2
	HB200	BLUE BLACK	49.45	929.25	197.8	3717.0
	HB444	BLUE	16.53	945.78	66.1	3783.1
	HB840	RED	15.45	961.23	61.8	3844.9
SLATE MET	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
	HB002	HYDRO BASE	577.65	577.65	2310.6	2310.6
	HB990	WHITE	423.13	1000.78	1692.5	4003.1
	HB250	BLACK	101.73	1102.50	406.9	4410.0
	HB002 Step 2	HYDRO BASE	588.85	1691.35	2355.4	6765.4
	HB861 Step 2	MAROON	131.95	1823.30	527.8	7293.2
	HB88M Step 2	SUPER RUSSET PEARL	51.35	1874.65	205.4	7498.6
	HB870 Step 2	MAGENTA	35.65	1910.30	142.6	7641.2
	HB88L Step 2	RUSSET PEARL	23.08	1933.38	92.3	7733.5
	HB250 Step 2	BLACK	17.78	1951.15	71.1	7804.6
SALSA RED PEARL, SALSA RED PEARL MET	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
	HB002	HYDRO BASE	492.78	492.78	1971.1	1971.1
	HB990	WHITE	673.38	1166.15	2693.5	4664.6
	HB259	LOW STRENGTH BLACK	13.27	1179.43	53.1	4717.7
	HB409	PHTHALO BLUE	12.08	1191.50	48.3	4766.0
	HB670	YELLOW OXIDE	3.63	1195.13	14.5	4780.5
	HB779	RED OXIDE	2.42	1197.55	9.7	4790.2
BIARRITZ WHITE, BIARRITZ WHITE MET	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
	HB002	HYDRO BASE	492.78	492.78	1971.1	1971.1
	HB990	WHITE	673.38	1166.15	2693.5	4664.6
	HB259	LOW STRENGTH BLACK	13.27	1179.43	53.1	4717.7
	HB409	PHTHALO BLUE	12.08	1191.50	48.3	4766.0
	HB670	YELLOW OXIDE	3.63	1195.13	14.5	4780.5
	HB779	RED OXIDE	2.42	1197.55	9.7	4790.2