






Dutch Star 2015

- SKIN: 54190 SAHARA GOLD MET.
- A - 62310 LABRADOR BLACK PEARL
- B - 705380A BROWN MET.
- C - 64147 SALSA RED PEARL

UNIT: 605199

DEALER: TOM JOHNSON CAMPING

SPECIAL: 710

PLEASE ACKNOWLEDGE AND DATE THE FOLLOWING ORDER/PRINT FOR APPROVAL TO BUILD, AND FAX TO NEWMAR (AT 574-773-2895) AS SOON AS POSSIBLE

DATE: _____

SIGN: _____

Paint Code Formulas - BASF *Diamont*

SPECIAL FOR UNIT # 605199 - 2015 DUTCH STAR

SKIN: 54190	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			Grams	Cum.	Grams	Cum. Grams
SAHARA GOLD MET	UR50	UNIVERSAL MID TEMP REDUCER	79.45	79.45	317.8	317.8
	BC101	FLOP CONTROL	15.68	95.13	62.7	380.5
	BC105	WHITE	8.75	103.88	35.0	415.5
	BC106	WHITE SATIN PEARL	59.38	163.25	237.5	653.0
	BC140	MEDIUM FINE IRIDESCENT	153.65	316.90	614.6	1267.6
	BC171	MEDIUM ALUMINUM	372.88	689.78	1491.5	2759.1
	BC200	BLACK	43.63	733.40	174.5	2933.6
	BC600	GOLD	112.63	846.03	450.5	3384.1
	BC800	RED GOLD	21.88	867.90	87.5	3471.6
	BC840	RED VIOLET	4.38	872.28	17.5	3489.1
COLOR A: 62310	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			Grams	Cum.	Grams	Cum. Grams
	UR50	UNIVERSAL MID TEMP REDUCER	78.90	78.90	315.6	315.6
	BC101	FLOP CONTROL	14.80	93.70	59.2	374.8
	BC105	WHITE	21.73	115.43	86.9	461.7
	BC200	BLACK	712.03	827.45	2848.1	3309.8
	BC605	YELLOW OXIDE	13.00	840.45	52.0	3361.8
	BC805	RED OXIDE	21.73	862.18	86.9	3448.7
	CB34M	VIOLET PEARL	2.63	864.80	10.5	3459.2
	CB44L	BRIGHT BLUE	2.63	867.43	10.5	3469.7
COLOR B: 705380 (705380A)	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			Grams	Cum.	Grams	Cum. Grams
	UR50	UNIVERSAL MID TEMP REDUCER	81.18	81.18	324.7	324.7
	BC800	RED GOLD	508.55	589.73	2034.2	2358.9
	BC605	YELLOW OXIDE	107.05	696.78	428.2	2787.1
	BC250	BLUE BLACK	85.63	782.40	342.5	3129.6
	BC201	DEEP BLACK	43.75	826.15	175.0	3304.6
	BC170	MEDIUM IRIDESCENT	29.43	855.58	117.7	3422.3
	BC171	MEDIUM ALUMINUM	21.43	877.00	85.7	3508.0
	BC180	COARSE IRIDESCENT	15.18	892.18	60.7	3568.7
COLOR C: 64147	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			Grams	Cum.	Grams	Cum. Grams
	UR50	UNIVERSAL MID TEMP REDUCER	80.73	80.73	322.9	322.9
	BC101	FLOP CONTROL	49.55	130.28	198.2	521.1
	BC105	WHITE	44.38	174.65	177.5	698.6
	BC116	SUPER RUSSET PEARL	212.63	387.28	850.5	1549.1
	BC200	BLACK	46.78	434.05	187.1	1736.2
	BC805	RED OXIDE	41.58	475.63	166.3	1902.5
	BC821	DARK MAROON	410.08	885.70	1640.3	3542.8
SALSA RED PEARL, SALSA RED PEARL MET	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			Grams	Cum.	Grams	Cum. Grams
	UR50	UNIVERSAL MID TEMP REDUCER	80.73	80.73	322.9	322.9
	BC101	FLOP CONTROL	49.55	130.28	198.2	521.1
	BC105	WHITE	44.38	174.65	177.5	698.6
	BC116	SUPER RUSSET PEARL	212.63	387.28	850.5	1549.1
	BC200	BLACK	46.78	434.05	187.1	1736.2
	BC805	RED OXIDE	41.58	475.63	166.3	1902.5
	BC821	DARK MAROON	410.08	885.70	1640.3	3542.8

Paint Code Formulas - BASF Onyx Waterborne

SPECIAL FOR UNIT # 605199 - 2015 DUTCH STAR

SKIN: 54190	SAHARA GOLD MET	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
		HB002	HYDRO BASE	610.48	610.48	2441.9	2441.9
		HB99K	WHITE SATIN PEARL	122.33	732.80	489.3	2931.2
		HB680	GOLD	99.58	832.38	398.3	3329.5
		HB150	MEDIUM ALUMINUM	77.03	909.40	308.1	3637.6
		HB99M	WHITE PEARL	31.75	941.15	127.0	3764.6
		HB110	ULTRA FINE ALUMINUM	10.25	951.40	41.0	3805.6
		HB203	DEEP BLACK	10.25	961.65	41.0	3846.6
		HB870	MAGENTA	6.75	968.40	27.0	3873.6
		HB090	FLOP CONTROL	18.13	986.53	72.5	3946.1
COLOR A: 62310	LABRADOR BLACK PEARL, LABRADOR BLACK MET	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
		HB002	HYDRO BASE	652.38	652.38	2609.5	2609.5
		HB203	DEEP BLACK	217.03	869.40	868.1	3477.6
		HB200	BLUE BLACK	32.30	901.70	129.2	3606.8
		HB670	YELLOW OXIDE	13.65	915.35	54.6	3661.4
		HB999	LOW STRENGTH WHITE	11.70	927.05	46.8	3708.2
		HB770	RED OXIDE	6.85	933.90	27.4	3735.6
		HB46L	BLUE PEARL	2.88	936.78	11.5	3747.1
		CB34M	VIOLET PEARL	2.95	939.73	11.8	3758.9
		HB740	BRIGHT ORANGE	1.98	941.70	7.9	3766.8
COLOR B: 705380	DRK GINGER MET	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
COLOR C: 64147	SALSA RED PEARL, SALSA RED PEARL MET	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
		HB002 Step 1	HYDRO BASE	577.65	577.65	2310.6	2310.6
		HB990 Step 1	WHITE	423.13	1000.78	1692.5	4003.1
		HB250 Step 1	BLACK	101.73	1102.50	406.9	4410.0
		HB002 Step 2	HYDRO BASE	588.85	1691.35	2355.4	6765.4
		HB861 Step 2	MAROON	131.95	1823.30	527.8	7293.2
		HB88M Step 2	SUPER RUSSET PEARL	51.35	1874.65	205.4	7498.6
		HB870 Step 2	MAGENTA	35.65	1910.30	142.6	7641.2
		HB88L Step 2	RUSSET PEARL	23.08	1933.38	92.3	7733.5
		HB250 Step 2	BLACK	17.78	1951.15	71.1	7804.6
		HB999 Step 2	LOW STRENGTH WHITE	8.38	1959.53	33.5	7838.1
		HB090 Step 2	FLOP CONTROL	93.23	2052.75	372.9	8211.0