





2015 Essex

15B200 DUSK

- SKIN: 62431 SILVER SHADOW PEARL
- A - 63227 NEWMAR ANTHRACITE MET.
- B - 62310 LABRADOR BLACK PEARL
- C - 60990A BIARRITZ WHITE MET.

AWNING: GIRARD
FABRIC: CHARCOAL TWEED
HARDWARE: BLACK

2015 ESSEX 15B200 - DUSK

[illegible]

Paint Code Formulas - BASF Onyx Waterborne

2015 ESSEX 15B200 - DUSK

SKIN: 62431	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			Grams	Cum.	Grams	Cum. Grams
SILVER SHADOW PEARL, SILVER SHADOW MET	HB002	HYDRO BASE	634.20	634.20	2536.8	2536.8
	HB64L	GOLD PEARL	94.57	728.78	378.3	2915.1
	HB110	ULTRA FINE ALUMINUM	87.90	816.68	351.6	3266.7
	HB120	FINE ALUMINUM	50.08	866.75	200.3	3467.0
	HB260	SATIN BLACK	37.80	904.55	151.2	3618.2
	HB150	MEDIUM ALUMINUM	14.45	919.00	57.8	3676.0
	HB780	RED GOLD	5.60	924.60	22.4	3698.4
	HB090	FLOP CONTROL	46.75	971.35	187.0	3885.4
COLOR A: 63227	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			Grams	Cum.	Grams	Cum. Grams
ANTHRACITE MET, NEWMAR ANTHRACITE MET	HB002	HYDRO BASE	626.60	626.60	2506.4	2506.4
	HB250	BLACK	132.88	759.48	531.5	3037.9
	HB200	BLUE BLACK	48.45	807.93	193.8	3231.7
	HB175	MEDIUM STARFLAKE ALUMINUM	39.10	847.03	156.4	3388.1
	HB444	BLUE	15.40	862.43	61.6	3449.7
	HB619	LIGHT YELLOW	13.38	875.80	53.5	3503.2
	HB46L	BLUE PEARL	8.23	884.03	32.9	3536.1
	CB34M	VIOLET PEARL	2.00	886.03	8.0	3544.1
	HB471	PHTHALO BLUE	2.08	888.10	8.3	3552.4
	HB090	FLOP CONTROL	62.85	950.95	251.4	3803.8
COLOR B: 62310	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			Grams	Cum.	Grams	Cum. Grams
LABRADOR BLACK PEARL, LABRADOR BLACK MET	HB002	HYDRO BASE	652.38	652.38	2609.5	2609.5
	HB203	DEEP BLACK	217.03	869.40	868.1	3477.6
	HB200	BLUE BLACK	32.30	901.70	129.2	3606.8
	HB670	YELLOW OXIDE	13.65	915.35	54.6	3661.4
	HB999	LOW STRENGTH WHITE	11.70	927.05	46.8	3708.2
	HB770	RED OXIDE	6.85	933.90	27.4	3735.6
	HB46L	BLUE PEARL	2.88	936.78	11.5	3747.1
	CB34M	VIOLET PEARL	2.95	939.73	11.8	3758.9
	HB740	BRIGHT ORANGE	1.98	941.70	7.9	3766.8
	HB090	FLOP CONTROL	12.70	954.40	50.8	3817.6
COLOR C: 60990 (60990A)	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			Grams	Cum.	Grams	Cum. Grams
BIARRITZ WHITE, BIARRITZ WHITE MET	HB002	HYDRO BASE	492.78	492.78	1971.1	1971.1
	HB990	WHITE	673.38	1166.15	2693.5	4664.6
	HB259	LOW STRENGTH BLACK	13.27	1179.43	53.1	4717.7
	HB409	PHTHALO BLUE	12.08	1191.50	48.3	4766.0
	HB670	YELLOW OXIDE	3.63	1195.13	14.5	4780.5
	HB779	RED OXIDE	2.42	1197.55	9.7	4790.2