




2016
Bay Star Sport

- SKIN: 64546C PEPPER WHITE
- A - 62310 LABRADOR BLACK PEARL
- B - 574482 ROSSO BORDEAU

UNIT: 111829
DEALER: Desert Autoplex
SPECIAL: 224

PLEASE ACKNOWLEDGE AND DATE THE FOLLOWING
ORDER/PRINT FOR APPROVAL TO BUILD, AND FAX TO
NEWMAR (AT 574-773-2895) AS SOON AS POSSIBLE

DATE: _____

SIGN: _____

Paint Code Formulas - BASF *Diamont*

SPECIAL FOR UNIT # 111829 - 2016 BAY STAR SPORT

SKIN: 64546 (64546C)	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			Grams	Cum.	Grams	Cum. Grams
PEPPER WHITE	UR50	UNIVERSAL MID TEMP REDUCER	78.93	78.93	315.7	315.7
	BC101	FLOP CONTROL	86.68	165.60	346.7	662.4
	BC191	0	724.35	889.95	2897.4	3559.8
	BC209	BLACK TONER	41.65	931.60	166.6	3726.4
	BC605	YELLOW OXIDE	22.55	954.15	90.2	3816.6
COLOR A: 62310	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			Grams	Cum.	Grams	Cum. Grams
LABRADOR BLACK PEARL, LABRADOR BLACK MET	UR50	UNIVERSAL MID TEMP REDUCER	78.90	78.90	315.6	315.6
	BC101	FLOP CONTROL	14.80	93.70	59.2	374.8
	BC105	WHITE	21.73	115.43	86.9	461.7
	BC200	BLACK	712.03	827.45	2848.1	3309.8
	BC605	YELLOW OXIDE	13.00	840.45	52.0	3361.8
	BC805	RED OXIDE	21.73	862.18	86.9	3448.7
	CB34M	VIOLET PEARL	2.63	864.80	10.5	3459.2
	CB44L	BRIGHT BLUE	2.63	867.43	10.5	3469.7
COLOR B: 574482	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			Grams	Cum.	Grams	Cum. Grams
ROSSO BORDEAU	UR50	UNIVERSAL MID TEMP REDUCER	79.53	79.53	318.1	318.1
	BC140	MEDIUM FINE IRIDESCENT	9.58	89.10	38.3	356.4
	BC170	MEDIUM IRIDESCENT	14.33	103.43	57.3	413.7
	BC300	CARBAZOLE VIOLET	104.13	207.55	416.5	830.2
	BC116	SUPER RUSSET PEARL	38.13	245.68	152.5	982.7
	BC200	BLACK	41.38	287.05	165.5	1148.2
	BC805	RED OXIDE	58.88	345.93	235.5	1383.7
	BC821	DARK MAROON	528.65	874.58	2114.6	3498.3

Paint Code Formulas - BASF Onyx Waterborne

SPECIAL FOR UNIT # 111829 - 2016 BAY STAR SPORT

SKIN: 64546 (64546C) PEPPER WHITE	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
	HB002	HYDRO BASE	495.08	495.08	1980.3	1980.3
	HB990	WHITE	590.40	1085.48	2361.6	4341.9
	HB259	LOW STRENGTH BLACK	67.05	1152.53	268.2	4610.1
	HB670	YELLOW OXIDE	15.65	1168.18	62.6	4672.7
COLOR A: 62310 LABRADOR BLACK PEARL, LABRADOR BLACK MET	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
	HB002	HYDRO BASE	652.38	652.38	2609.5	2609.5
	HB203	DEEP BLACK	217.03	869.40	868.1	3477.6
	HB200	BLUE BLACK	32.30	901.70	129.2	3606.8
	HB670	YELLOW OXIDE	13.65	915.35	54.6	3661.4
	HB999	LOW STRENGTH WHITE	11.70	927.05	46.8	3708.2
	HB770	RED OXIDE	6.85	933.90	27.4	3735.6
	HB46L	BLUE PEARL	2.88	936.78	11.5	3747.1
	CB34M	VIOLET PEARL	2.95	939.73	11.8	3758.9
	HB740	BRIGHT ORANGE	1.98	941.70	7.9	3766.8
	HB090	FLOP CONTROL	12.70	954.40	50.8	3817.6
COLOR B: 574482 ROSSO BORDEAU	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
	HB002 Step 1	HYDRO BASE	537.30	537.30	2149.2	2149.2
	HB990 Step 1	WHITE	565.23	1102.53	2260.9	4410.1
	HB250 Step 1	BLACK	53.63	1156.15	214.5	4624.6
	HB002 Step 2	HYDRO BASE	622.75	1778.90	2491.0	7115.6
	HB861 Step 2	MAROON	208.83	1987.73	835.3	7950.9
	HB300 Step 2	CARBAZOLE VIOLET	46.35	2034.08	185.4	8136.3
	HB88L Step 2	RUSSET PEARL	29.93	2064.00	119.7	8256.0
	HB740 Step 2	BRIGHT ORANGE	18.38	2082.38	73.5	8329.5
	HB200 Step 2	BLUE BLACK	13.55	2095.93	54.2	8383.7
	HB961 Step 2	TRANSPARENT WHITE	7.68	2103.60	30.7	8414.4
	HB130 Step 2	FINE ALUMINUM	1.92	2105.53	7.7	8422.1
	HB090 Step 2	FLOP CONTROL	4.80	2110.33	19.2	8441.3