






2016 *Bay Star*

- SKIN: 53013A SAHARA BEIGE MET
- A - 64443 PEARL BLACK MET.
- B - 54675A MEDIUM GREY MET.
- C - 60990A BIARRITZ WHITE MET.

UNIT: 111830

DEALER: Desert Autoplex

SPECIAL: 237

PLEASE ACKNOWLEDGE AND DATE THE FOLLOWING
ORDER/PRINT FOR APPROVAL TO BUILD, AND FAX TO
NEWMAR (AT 574-773-2895) AS SOON AS POSSIBLE

DATE: _____

SIGN: _____

SPECIAL FOR UNIT # 111830 - 2016 BAY STAR

[illegible]

Paint Code Formulas - BASF Onyx Waterborne

SPECIAL FOR UNIT # 111830 - 2016 BAY STAR

SKIN: 53013 (53013A) SAHARA BEIGE MET	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			<i>Grams</i>	<i>Cum.</i>	<i>Grams</i>	<i>Cum. Grams</i>
	HB002	HYDRO BASE	643.70	643.70	2574.8	2574.8
	HB110	ULTRA FINE ALUMINUM	149.33	793.03	597.3	3172.1
	HB680	GOLD	59.30	852.33	237.2	3409.3
	HB259	LOW STRENGTH BLACK	30.68	883.00	122.7	3532.0
	HB140	MEDIUM ALUMINUM	27.53	910.53	110.1	3642.1
	HB999	LOW STRENGTH WHITE	16.95	927.48	67.8	3709.9
	HB99M	WHITE PEARL	10.55	938.03	42.2	3752.1
	HB861	MAROON	9.55	947.58	38.2	3790.3
	HB670	YELLOW OXIDE	6.42	954.00	25.7	3816.0
	HB090	FLOP CONTROL	11.65	965.65	46.6	3862.6
COLOR A: 64443 PEARL BLACK, BLACK PEARL MET	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			<i>Grams</i>	<i>Cum.</i>	<i>Grams</i>	<i>Cum. Grams</i>
	HB002	HYDRO BASE	665.58	665.58	2662.3	2662.3
	HB203	DEEP BLACK	211.58	877.15	846.3	3508.6
	HB46L	BLUE PEARL	31.33	908.48	125.3	3633.9
	HB99L	CRYSTAL WHITE	19.55	928.03	78.2	3712.1
	HB670	YELLOW OXIDE	13.65	941.68	54.6	3766.7
	HB999	LOW STRENGTH WHITE	3.93	945.60	15.7	3782.4
	HB150	MEDIUM ALUMINUM	2.95	948.55	11.8	3794.2
	HB090	FLOP CONTROL	8.85	957.40	35.4	3829.6
COLOR B: 54675 MEDIUM GREY MET	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			<i>Grams</i>	<i>Cum.</i>	<i>Grams</i>	<i>Cum. Grams</i>
COLOR C: 60990 (60990A) BIARRITZ WHITE, BIARRITZ WHITE MET	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			<i>Grams</i>	<i>Cum.</i>	<i>Grams</i>	<i>Cum. Grams</i>
	HB002	HYDRO BASE	492.78	492.78	1971.1	1971.1
	HB990	WHITE	673.38	1166.15	2693.5	4664.6
	HB259	LOW STRENGTH BLACK	13.27	1179.43	53.1	4717.7
	HB409	PHTHALO BLUE	12.08	1191.50	48.3	4766.0
	HB670	YELLOW OXIDE	3.63	1195.13	14.5	4780.5
	HB779	RED OXIDE	2.42	1197.55	9.7	4790.2