






"OMIT FADES"



2016
LONDONAIRE

- SKIN: 575874A EGGSHELL
- A - 62447 NEWMAR BROWN MICA
- B - 64443 PEARL BLACK MET.
- C - 60751B PANAMA BROWN PEARL

UNIT: 501301
DEALER: NORTH TRAIL RV
SPECIAL: 585 (Rev 2)

PLEASE ACKNOWLEDGE AND DATE THE FOLLOWING
ORDER/PRINT FOR APPROVAL TO BUILD, AND FAX TO
NEWMAR (AT 574-773-2895) AS SOON AS POSSIBLE

DATE: _____

SIGN: _____

Paint Code Formulas - BASF *Diamont*

SPECIAL FOR UNIT # 501301 - 2016 LONDON AIRE

SKIN: 575874 (575874A)	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			Grams	Cum.	Grams	Cum. Grams
EGGSHELL	UR50	UNIVERSAL MID TEMP REDUCER	79.03	79.03	316.1	316.1
	BC191	0	733.45	812.48	2933.8	3249.9
	BC209	BLACK TONER	27.08	839.55	108.3	3358.2
	BC605	YELLOW OXIDE	24.55	864.10	98.2	3456.4
	BC805	RED OXIDE	4.33	868.43	17.3	3473.7
	BC101	FLOP CONTROL	87.15	955.58	348.6	3822.3
COLOR A: 62447	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			Grams	Cum.	Grams	Cum. Grams
BROWN MICA, BROWN MICA MET	UR50	UNIVERSAL MID TEMP REDUCER	72.48	72.48	289.9	289.9
	BC101	FLOP CONTROL	48.30	120.78	193.2	483.1
	BC171	MEDIUM ALUMINUM	243.00	363.78	972.0	1455.1
	BC175	MEDIUM STARFLAKE ALUMINUM	32.60	396.38	130.4	1585.5
	BC200	BLACK	399.03	795.40	1596.1	3181.6
	BC800	RED GOLD	35.28	830.68	141.1	3322.7
	BC821	DARK MAROON	27.78	858.45	111.1	3433.8
	BC610	GREEN GOLD	10.88	869.33	43.5	3477.3
COLOR B: 64443	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			Grams	Cum.	Grams	Cum. Grams
PEARL BLACK, BLACK PEARL MET	UR50	UNIVERSAL MID TEMP REDUCER	80.35	80.35	321.4	321.4
	BC105	WHITE	7.30	87.65	29.2	350.6
	BC118	BLUE PEARL	32.48	120.13	129.9	480.5
	BC1190	CRYSTAL WHITE	36.13	156.25	144.5	625.0
	BC171	MEDIUM ALUMINUM	4.88	161.13	19.5	644.5
	BC200	BLACK	674.85	835.98	2699.4	3343.9
	BC410	GREEN BLUE	11.78	847.75	47.1	3391.0
	BC805	RED OXIDE	12.58	860.33	50.3	3441.3
	BC101	FLOP CONTROL	8.93	869.25	35.7	3477.0
COLOR C: 60751 (60751B)	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			Grams	Cum.	Grams	Cum. Grams
PANAMA BROWN PEARL, PANAMA BROWN MET	UR50	UNIVERSAL MID TEMP REDUCER	79.88	79.88	319.5	319.5
	BC800	RED GOLD	264.20	344.08	1056.8	1376.3
	BC200	BLACK	172.05	516.13	688.2	2064.5
	BC170	MEDIUM IRIDESCENT	92.18	608.30	368.7	2433.2
	BC821	DARK MAROON	270.35	878.65	1081.4	3514.6

Paint Code Formulas - BASF Onyx Waterborne

SPECIAL FOR UNIT # 501301 - 2016 LONDON AIRE

SKIN: 575874 (575874A)	EGGSHELL	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
		HB002	HYDRO BASE	492.50	492.50	1970.0	1970.0
		HB990	WHITE	504.30	996.80	2017.2	3987.2
		HB779	RED OXIDE	65.05	1061.85	260.2	4247.4
		HB259	LOW STRENGTH BLACK	54.13	1115.98	216.5	4463.9
		HB670	YELLOW OXIDE	21.73	1137.70	86.9	4550.8
COLOR A: 62447	BROWN MICA, BROWN MICA MET	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
		HB002	HYDRO BASE	614.10	614.10	2456.4	2456.4
		HB203	DEEP BLACK	117.85	731.95	471.4	2927.8
		HB150	MEDIUM ALUMINUM	69.75	801.70	279.0	3206.8
		HB110	ULTRA FINE ALUMINUM	26.40	828.10	105.6	3312.4
		HB780	RED GOLD	21.65	849.75	86.6	3399.0
		HB880	RED VIOLET	13.25	863.00	53.0	3452.0
		HB861	MAROON	10.85	873.85	43.4	3495.4
		HB090	FLOP CONTROL	80.53	954.38	322.1	3817.5
COLOR B: 64443	PEARL BLACK, BLACK PEARL MET	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
		HB002	HYDRO BASE	665.58	665.58	2662.3	2662.3
		HB203	DEEP BLACK	211.58	877.15	846.3	3508.6
		HB46L	BLUE PEARL	31.33	908.48	125.3	3633.9
		HB99L	CRYSTAL WHITE	19.55	928.03	78.2	3712.1
		HB670	YELLOW OXIDE	13.65	941.68	54.6	3766.7
		HB999	LOW STRENGTH WHITE	3.93	945.60	15.7	3782.4
		HB150	MEDIUM ALUMINUM	2.95	948.55	11.8	3794.2
		HB090	FLOP CONTROL	8.85	957.40	35.4	3829.6
COLOR C: 60751 (60751B)	PANAMA BROWN PEARL, PANAMA BROWN MET	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
		HB002	HYDRO BASE	570.40	570.40	2281.6	2281.6
		HB780	RED GOLD	145.13	715.53	580.5	2862.1
		HB680	GOLD	107.78	823.30	431.1	3293.2
		HB861	MAROON	71.40	894.70	285.6	3578.8
		HB88M	SUPER RUSSET PEARL	38.47	933.18	153.9	3732.7
		HB203	DEEP BLACK	28.63	961.80	114.5	3847.2
		HB999	LOW STRENGTH WHITE	19.78	981.58	79.1	3926.3
		HB175	MEDIUM STARFLAKE ALUMINUM	6.60	988.18	26.4	3952.7