






2016 KING AIRE

16B120 ROYAL MIST

- SKIN: 51291 LIGHT SANDRIFT MET.
- A - 57714 DARK FAWN MET.
- B - 62930 ONYX MET.
- C - 60751B PANAMA BROWN PEARL

AWNING: GIRARD NOVA
FABRIC: WALNUT BROWN
HARDWARE: BLACK

Paint Code Formulas - BASF *Diamont*

2016 KING AIRE 16B120 - ROYAL MIST

SKIN: 51291	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			<i>Grams</i>	<i>Cum.</i>	<i>Grams</i>	<i>Cum. Grams</i>
LT. SANDRIFT MET, LT. SANDRIFT	UR50	UNIVERSAL MID TEMP REDUCER	79.25	79.25	317.0	317.0
	BC101	FLOP CONTROL	30.48	109.73	121.9	438.9
	BC140	MEDIUM FINE IRIDESCENT	100.20	209.93	400.8	839.7
	BC171	MEDIUM ALUMINUM	499.08	709.00	1996.3	2836.0
	BC195	TRANSPARENT WHITE	28.75	737.75	115.0	2951.0
	BC201	DEEP BLACK	73.20	810.95	292.8	3243.8
	BC250	BLUE BLACK	32.28	843.23	129.1	3372.9
	BC800	RED GOLD	26.13	869.35	104.5	3477.4
	BC840	RED VIOLET	1.73	871.08	6.9	3484.3
COLOR A: 57714	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			<i>Grams</i>	<i>Cum.</i>	<i>Grams</i>	<i>Cum. Grams</i>
DARK FAWN MET	UR50	UNIVERSAL MID TEMP REDUCER	78.38	78.38	313.5	313.5
	BC200	BLACK	539.75	618.13	2159.0	2472.5
	BC140	MEDIUM FINE IRIDESCENT	81.75	699.88	327.0	2799.5
	BC105	WHITE	53.98	753.85	215.9	3015.4
	BC101	FLOP CONTROL	52.18	806.03	208.7	3224.1
	BC180	COARSE IRIDESCENT	37.38	843.40	149.5	3373.6
	BC821	DARK MAROON	9.60	853.00	38.4	3412.0
	BC805	RED OXIDE	7.80	860.80	31.2	3443.2
	BC800	RED GOLD	6.00	866.80	24.0	3467.2
COLOR B: 62930	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			<i>Grams</i>	<i>Cum.</i>	<i>Grams</i>	<i>Cum. Grams</i>
ONYX MET	UR50	UNIVERSAL MID TEMP REDUCER	78.75	78.75	315.0	315.0
	BC200	BLACK	644.83	723.58	2579.3	2894.3
	BC600	GOLD	47.58	771.15	190.3	3084.6
	BC105	WHITE	40.78	811.93	163.1	3247.7
	BC805	RED OXIDE	32.98	844.90	131.9	3379.6
	BC140	MEDIUM FINE IRIDESCENT	11.20	856.10	44.8	3424.4
	BC101	FLOP CONTROL	8.60	864.70	34.4	3458.8
	BC171	MEDIUM ALUMINUM	1.80	866.50	7.2	3466.0
COLOR C: 60751 (60751B)	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			<i>Grams</i>	<i>Cum.</i>	<i>Grams</i>	<i>Cum. Grams</i>
PANAMA BROWN PEARL, PANAMA BROWN MET	UR50	UNIVERSAL MID TEMP REDUCER	79.88	79.88	319.5	319.5
	BC800	RED GOLD	264.20	344.08	1056.8	1376.3
	BC200	BLACK	172.05	516.13	688.2	2064.5
	BC170	MEDIUM IRIDESCENT	92.18	608.30	368.7	2433.2
	BC821	DARK MAROON	270.35	878.65	1081.4	3514.6

Paint Code Formulas - BASF Onyx Waterborne

2016 KING AIRE 16B120 - ROYAL MIST

SKIN: 51291 LIGHT SANDRIFT MET, LT. SANDRIFT	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
	HB002	HYDRO BASE	623.03	623.03	2492.1	2492.1
	HB64L	GOLD PEARL	138.58	761.60	554.3	3046.4
	HB150	MEDIUM ALUMINUM	107.30	868.90	429.2	3475.6
	HB250	BLACK	53.63	922.53	214.5	3690.1
	HB999	LOW STRENGTH WHITE	13.43	935.95	53.7	3743.8
	HB780	RED GOLD	5.60	941.55	22.4	3766.2
	HB090	FLOP CONTROL	34.65	976.20	138.6	3904.8
COLOR A: 57714 DARK FAWN MET	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
	HB002	HYDRO BASE	613.45	613.45	2453.8	2453.8
	HB203	DEEP BLACK	163.10	776.55	652.4	3106.2
	HB999	LOW STRENGTH WHITE	27.05	803.60	108.2	3214.4
	HB110	ULTRA FINE ALUMINUM	15.57	819.18	62.3	3276.7
	HB140	MEDIUM ALUMINUM	14.55	833.73	58.2	3334.9
	HB861	MAROON	8.35	842.08	33.4	3368.3
	HB770	RED OXIDE	6.22	848.30	24.9	3393.2
	HB090	FLOP CONTROL	96.63	944.93	386.5	3779.7
COLOR B: 62930 ONYX MET	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
	HB002	HYDRO BASE	667.48	667.48	2669.9	2669.9
	HB250	BLACK	197.70	865.18	790.8	3460.7
	HB200	BLUE BLACK	38.00	903.18	152.0	3612.7
	HB650	YELLOW GOLD	31.13	934.30	124.5	3737.2
	HB999	LOW STRENGTH WHITE	7.78	942.08	31.1	3768.3
	HB770	RED OXIDE	5.80	947.88	23.2	3791.5
	HB120	FINE ALUMINUM	1.05	948.93	4.2	3795.7
COLOR C: 60751 (60751B) PANAMA BROWN PEARL, PANAMA BROWN MET	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
	HB002	HYDRO BASE	570.40	570.40	2281.6	2281.6
	HB780	RED GOLD	145.13	715.53	580.5	2862.1
	HB680	GOLD	107.78	823.30	431.1	3293.2
	HB861	MAROON	71.40	894.70	285.6	3578.8
	HB88M	SUPER RUSSET PEARL	38.47	933.18	153.9	3732.7
	HB203	DEEP BLACK	28.63	961.80	114.5	3847.2
	HB999	LOW STRENGTH WHITE	19.78	981.58	79.1	3926.3
	HB175	MEDIUM STARFLAKE ALUMINUM	6.60	988.18	26.4	3952.7