





2017 *Bay Star*

- SKIN: 44429B LIGHT CHAMPAGNE MET.
- A - 60990A BIARRITZ WHITE MET.
- B - 574482 ROSSO BORDEAU
- C - 56680 CAJUN SPICE OBSIDIAN

UNIT: 112364

DEALER: HOLLAND MOTOR HOMES

SPECIAL: 521

PLEASE ACKNOWLEDGE AND DATE THE FOLLOWING
ORDER/PRINT FOR APPROVAL TO BUILD, AND FAX TO
NEWMAR (AT 574-773-2895) AS SOON AS POSSIBLE

DATE: _____

SIGN: _____

Paint Code Formulas - BASF Diamont

SPECIAL FOR UNIT # 112364 - 2017 BAY STAR

SKIN: 44429 (44429B)	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			Grams	Cum.	Grams	Cum. Grams
LIGHT CHAMPAGNE MET	UR50	UNIVERSAL MID TEMP REDUCER	83.70	83.70	334.8	334.8
	BC821	DARK MAROON	6.00	89.70	24.0	358.8
	BC101	FLOP CONTROL	103.85	193.55	415.4	774.2
	BC170	MEDIUM IRIDESCENT	174.03	367.58	696.1	1470.3
	BC194	HI HIDING WHITE	10.98	378.55	43.9	1514.2
	BC171	MEDIUM ALUMINUM	405.40	783.95	1621.6	3135.8
	BC800	RED GOLD	43.48	827.43	173.9	3309.7
	BC250	BLUE BLACK	46.68	874.10	186.7	3496.4
COLOR A: #N/A	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
#N/A	#N/A		#N/A	#N/A	#N/A	#N/A
	#N/A		#N/A	#N/A	#N/A	#N/A
	#N/A		#N/A	#N/A	#N/A	#N/A
	#N/A		#N/A	#N/A	#N/A	#N/A
	#N/A		#N/A	#N/A	#N/A	#N/A
	#N/A		#N/A	#N/A	#N/A	#N/A
	#N/A		#N/A	#N/A	#N/A	#N/A
	#N/A		#N/A	#N/A	#N/A	#N/A
	#N/A		#N/A	#N/A	#N/A	#N/A
	#N/A		#N/A	#N/A	#N/A	#N/A
COLOR B: 574482	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
ROSSO BORDEAU	UR50	UNIVERSAL MID TEMP REDUCER	79.53	79.53	318.1	318.1
	BC140	MEDIUM FINE IRIDESCENT	9.58	89.10	38.3	356.4
	BC170	MEDIUM IRIDESCENT	14.33	103.43	57.3	413.7
	BC300	CARBAZOLE VIOLET	104.13	207.55	416.5	830.2
	BC116	SUPER RUSSET PEARL	38.13	245.68	152.5	982.7
	BC200	BLACK	41.38	287.05	165.5	1148.2
	BC805	RED OXIDE	58.88	345.93	235.5	1383.7
	BC821	DARK MAROON	528.65	874.58	2114.6	3498.3
COLOR C: 56680B	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
CAJON SPICE OBSIDIAN PEARL, OBSIDIAN BLACK MET	UR50	UNIVERSAL MID TEMP REDUCER	79.00	79.00	316.0	316.0
	BC200	BLACK	640.25	719.25	2561.0	2877.0
	BC471		54.00	773.25	216.0	3093.0
	BC105	WHITE	41.20	814.45	164.8	3257.8
	BC809		12.80	827.25	51.2	3309.0
	BC825	LIGHT MAROON	13.00	840.25	52.0	3361.0
	BC140	MEDIUM FINE IRIDESCENT	12.00	852.25	48.0	3409.0
	BC609		6.00	858.25	24.0	3433.0

SKIN: 44429 (44429A)		BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
LIGHT CHAMPAGNE MET		HB002	HYDRO BASE	598.90	598.90	2395.6	2395.6
		HB130	FINE ALUMINUM	120.23	719.13	480.9	2876.5
		HB150	MEDIUM ALUMINUM	86.10	805.23	344.4	3220.9
		HB999	LOW STRENGTH WHITE	66.23	871.45	264.9	3485.8
		HB780	RED GOLD	29.78	901.23	119.1	3604.9
		HB200	BLUE BLACK	19.85	921.08	79.4	3684.3
		HB861	MAROON	6.67	927.75	26.7	3711.0
		HB090	FLOP CONTROL	47.45	975.20	189.8	3900.8
COLOR A: #N/A		BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
#N/A		#N/A		#N/A	#N/A	#N/A	#N/A
		#N/A		#N/A	#N/A	#N/A	#N/A
		#N/A		#N/A	#N/A	#N/A	#N/A
		#N/A		#N/A	#N/A	#N/A	#N/A
		#N/A		#N/A	#N/A	#N/A	#N/A
		#N/A		#N/A	#N/A	#N/A	#N/A
		#N/A		#N/A	#N/A	#N/A	#N/A
		#N/A		#N/A	#N/A	#N/A	#N/A
		#N/A		#N/A	#N/A	#N/A	#N/A
		#N/A		#N/A	#N/A	#N/A	#N/A
		#N/A		#N/A	#N/A	#N/A	#N/A
COLOR B: 574482		BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
ROSSO BORDEAU		HB002 Step 1	HYDRO BASE	537.30	537.30	2149.2	2149.2
		HB990 Step 1	WHITE	565.23	1102.53	2260.9	4410.1
		HB250 Step 1	BLACK	53.63	1156.15	214.5	4624.6
		HB002 Step 2	HYDRO BASE	622.75	1778.90	2491.0	7115.6
		HB861 Step 2	MAROON	208.83	1987.73	835.3	7950.9
		HB300 Step 2	CARBAZOLE VIOLET	46.35	2034.08	185.4	8136.3
		HB88L Step 2	RUSSET PEARL	29.93	2064.00	119.7	8256.0
		HB740 Step 2	BRIGHT ORANGE	18.38	2082.38	73.5	8329.5
		HB200 Step 2	BLUE BLACK	13.55	2095.93	54.2	8383.7
		HB961 Step 2	TRANSPARENT WHITE	7.68	2103.60	30.7	8414.4
		HB130 Step 2	FINE ALUMINUM	1.92	2105.53	7.7	8422.1
		HB090 Step 2	FLOP CONTROL	4.80	2110.33	19.2	8441.3
COLOR C: 56680		BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
CAJON SPICE OBSIDIAN PEARL, OBSIDIAN BLACK MET		HB002	HYDRO BASE	665.33	665.33	2661.3	2661.3
		HB203	DEEP BLACK	227.93	893.25	911.7	3573.0
		HB200	BLUE BLACK	20.25	913.50	81.0	3654.0
		HB770	RED OXIDE	11.63	925.13	46.5	3700.5
		HB670	YELLOW OXIDE	9.70	934.83	38.8	3739.3
		HB999	LOW STRENGTH WHITE	8.67	943.50	34.7	3774.0
		HB462	SAPPHIRE 2	5.85	949.35	23.4	3797.4
		HB150	MEDIUM ALUMINUM	2.00	951.35	8.0	3805.4
		HB130	FINE ALUMINUM	1.92	953.28	7.7	3813.1