



2017

LONDONAIRE

SKIN: 62447 NEWMAR BROWN MICA
A - 44429B LIGHT CHAMPAGNE MET.
B - 61881 MERLOT RED MET.
C - 64546C PEPPER WHITE

UNIT: 501487
DEALER: Steinbring Motorcoach
SPECIAL: 1114

PLEASE ACKNOWLEDGE AND DATE THE FOLLOWING ORDER/PRINT FOR APPROVAL TO BUILD, AND FAX TO NEWMAR (AT 574-773-2895) AS SOON AS POSSIBLE

DATE: _____

SIGN: _____

Paint Code Formulas - BASF *Diamont*

SPECIAL FOR UNIT # 501487 - 2017 LONDON AIRE

SKIN: 62447

BROWN MICA, BROWN MICA MET

BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
UR50	UNIVERSAL MID TEMP REDUCER	72.48	72.48	289.9	289.9
BC101	FLOP CONTROL	48.30	120.78	193.2	483.1
BC171	MEDIUM ALUMINUM	243.00	363.78	972.0	1455.1
BC175	MEDIUM STARFLAKE ALUMINUM	32.60	396.38	130.4	1585.5
BC200	BLACK	399.03	795.40	1596.1	3181.6
BC800	RED GOLD	35.28	830.68	141.1	3322.7
BC821	DARK MAROON	27.78	858.45	111.1	3433.8
BC610	GREEN GOLD	10.88	869.33	43.5	3477.3

COLOR A: 44429 (44429B)

LIGHT CHAMPAGNE MET

BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
UR50	UNIVERSAL MID TEMP REDUCER	83.70	83.70	334.8	334.8
BC821	DARK MAROON	6.00	89.70	24.0	358.8
BC101	FLOP CONTROL	103.85	193.55	415.4	774.2
BC170	MEDIUM IRIDESCENT	174.03	367.58	696.1	1470.3
BC194	HI HIDING WHITE	10.98	378.55	43.9	1514.2
BC171	MEDIUM ALUMINUM	405.40	783.95	1621.6	3135.8
BC800	RED GOLD	43.48	827.43	173.9	3309.7
BC250	BLUE BLACK	46.68	874.10	186.7	3496.4

COLOR B: 61881

MERLOT RED PEARL, MERLOT RED MET

BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
UR50	UNIVERSAL MID TEMP REDUCER	81.80	81.80	327.2	327.2
BC101	FLOP CONTROL	11.58	93.38	46.3	373.5
BC1815	CRYSTAL RED	119.30	212.68	477.2	850.7
BC201	DEEP BLACK	106.93	319.60	427.7	1278.4
BC821	DARK MAROON	387.03	706.63	1548.1	2826.5
BC832	RED	86.98	793.60	347.9	3174.4
BC840	RED VIOLET	78.20	871.80	312.8	3487.2
CB34M	VIOLET PEARL	7.98	879.78	31.9	3519.1

COLOR C: 64546 (64546C)

PEPPER WHITE

BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
UR50	UNIVERSAL MID TEMP REDUCER	78.93	78.93	315.7	315.7
BC101	FLOP CONTROL	86.68	165.60	346.7	662.4
BC191	0	724.35	889.95	2897.4	3559.8
BC209	BLACK TONER	41.65	931.60	166.6	3726.4
BC605	YELLOW OXIDE	22.55	954.15	90.2	3816.6

Paint Code Formulas - BASF *Onyx Waterborne*

SPECIAL FOR UNIT # 501487 - 2017 LONDON AIRE

SKIN: 62447

BROWN MICA, BROWN MICA MET

BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
HB002	HYDRO BASE	614.10	614.10	2456.4	2456.4
HB203	DEEP BLACK	117.85	731.95	471.4	2927.8
HB150	MEDIUM ALUMINUM	69.75	801.70	279.0	3206.8
HB110	ULTRA FINE ALUMINUM	26.40	828.10	105.6	3312.4
HB780	RED GOLD	21.65	849.75	86.6	3399.0
HB880	RED VIOLET	13.25	863.00	53.0	3452.0
HB861	MAROON	10.85	873.85	43.4	3495.4
HB090	FLOP CONTROL	80.53	954.38	322.1	3817.5

COLOR A: 44429 (44429A)

LIGHT CHAMPAGNE MET

BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
HB002	HYDRO BASE	598.90	598.90	2395.6	2395.6
HB130	FINE ALUMINUM	120.23	719.13	480.9	2876.5
HB150	MEDIUM ALUMINUM	86.10	805.23	344.4	3220.9
HB999	LOW STRENGTH WHITE	66.23	871.45	264.9	3485.8
HB780	RED GOLD	29.78	901.23	119.1	3604.9
HB200	BLUE BLACK	19.85	921.08	79.4	3684.3
HB861	MAROON	6.67	927.75	26.7	3711.0
HB090	FLOP CONTROL	47.45	975.20	189.8	3900.8

COLOR B: 61881

MERLOT RED PEARL, MERLOT RED MET

BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
HB002 Step 1	HYDRO BASE	653.75	653.75	2615.0	2615.0
HB250 Step 1	BLACK	192.38	846.13	769.5	3384.5
HB990 Step 1	WHITE	155.20	1001.33	620.8	4005.3
HB002 Step 2	HYDRO BASE	626.35	1627.68	2505.4	6510.7
HB861 Step 2	MAROON	120.18	1747.85	480.7	6991.4
HB870 Step 2	MAGENTA	83.00	1830.85	332.0	7323.4
HB840 Step 2	RED	67.75	1898.60	271.0	7594.4
HB203 Step 2	DEEP BLACK	30.48	1929.08	121.9	7716.3
HB88N Step 2	CRYSTAL RED	21.03	1950.10	84.1	7800.4

COLOR C: 64546 (64546C)

PEPPER WHITE

BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
HB002	HYDRO BASE	495.08	495.08	1980.3	1980.3
HB990	WHITE	590.40	1085.48	2361.6	4341.9
HB259	LOW STRENGTH BLACK	67.05	1152.53	268.2	4610.1
HB670	YELLOW OXIDE	15.65	1168.18	62.6	4672.7