



2017

LONDONAIRE

SKIN: 62500 BRIGHT PLATINUM MET.
A - 60990A BIARRITZ WHITE MET.
B - 41100 CHARCOAL PEARL
C - 64147 SALSA RED PEARL

UNIT: 501501
DEALER: Desert Autoplex
SPECIAL: 1832

PLEASE ACKNOWLEDGE AND DATE THE FOLLOWING ORDER/PRINT FOR APPROVAL TO BUILD, AND FAX TO NEWMAR (AT 574-773-2895) AS SOON AS POSSIBLE

DATE: _____

SIGN: _____

Paint Code Formulas - BASF *Diamont*

SPECIAL FOR UNIT 501501 - 2017 LONDON AIRE

SKIN: 62500

BRIGHT PLATINUM MET

BASE #	BASE NAME	1 QT Grams	1 QUART Cum. Grams	1 GAL Grams	1 GALLON Cum. Grams
UR50	UNIVERSAL MID TEMP REDUCER	79.88	79.88	319.5	319.5
BC101	FLOP CONTROL	41.20	121.08	164.8	484.3
BC105	WHITE	65.83	186.90	263.3	747.6
BC171	MEDIUM ALUMINUM	204.38	391.28	817.5	1565.1
BC180	COARSE IRIDESCENT	226.30	617.58	905.2	2470.3
BC195	TRANSPARENT WHITE	28.93	646.50	115.7	2586.0
BC200	BLACK	75.48	721.98	301.9	2887.9
BC250	BLUE BLACK	117.53	839.50	470.1	3358.0
BC260	SATIN BLACK	37.78	877.28	151.1	3509.1

COLOR A: 60990 (60990A)

BIARRITZ WHITE MET

BASE #	BASE NAME	1 QT Grams	1 QUART Cum. Grams	1 GAL Grams	1 GALLON Cum. Grams
UR50	UNIVERSAL MID TEMP REDUCER	84.13	84.13	336.5	336.5
BC194	HI HIDING WHITE	938.38	1022.50	3753.5	4090.0
BC209	BLACK TONER	28.53	1051.03	114.1	4204.1
BC605	YELLOW OXIDE	13.55	1064.58	54.2	4258.3

COLOR B: 41100

CHARCOAL PEARL

BASE #	BASE NAME	1 QT Grams	1 QUART Cum. Grams	1 GAL Grams	1 GALLON Cum. Grams
UR50	UNIVERSAL MID TEMP REDUCER	83.25	83.25	333.0	333.0
BC101	FLOP CONTROL	68.95	152.20	275.8	608.8
BC110	WHITE PEARL	88.68	240.88	354.7	963.5
BC171	MEDIUM ALUMINUM	196.08	436.95	784.3	1747.8
BC200	BLACK	318.38	755.33	1273.5	3021.3
BC300	CARBAZOLE VIOLET	48.60	803.93	194.4	3215.7
BC402	PHTHALO BLUE	50.48	854.40	201.9	3417.6
BC805	RED OXIDE	15.10	869.50	60.4	3478.0

COLOR C: 64147

SALSA RED PEARL MET

BASE #	BASE NAME	1 QT Grams	1 QUART Cum. Grams	1 GAL Grams	1 GALLON Cum. Grams
UR50	UNIVERSAL MID TEMP REDUCER	80.73	80.73	322.9	322.9
BC101	FLOP CONTROL	49.55	130.28	198.2	521.1
BC105	WHITE	44.38	174.65	177.5	698.6
BC116	SUPER RUSSET PEARL	212.63	387.28	850.5	1549.1
BC200	BLACK	46.78	434.05	187.1	1736.2
BC805	RED OXIDE	41.58	475.63	166.3	1902.5
BC821	DARK MAROON	410.08	885.70	1640.3	3542.8

Paint Code Formulas - BASF *Onyx Waterborne*

SPECIAL FOR UNIT 501501 - 2017 LONDON AIRE

SKIN: 62500

BRIGHT PLATINUM MET

BASE #	BASE NAME	1 QT Grams	1 QUART Cum. Grams	1 GAL Grams	1 GALLON Cum. Grams
HB002	HYDRO BASE	618.75	618.75	2475.0	2475.0
HB140	MEDIUM ALUMINUM	82.28	701.03	329.1	2804.1
HB120	FINE ALUMINUM	77.95	778.98	311.8	3115.9
HB200	BLUE BLACK	78.03	857.00	312.1	3428.0
HB203	DEEP BLACK	24.93	881.93	99.7	3527.7
HB260	SATIN BLACK	22.78	904.70	91.1	3618.8
HB999	LOW STRENGTH WHITE	19.47	924.18	77.9	3696.7
HB961	TRANSPARENT WHITE	15.13	939.30	60.5	3757.2
HB090	FLOP CONTROL	32.48	971.78	129.9	3887.1

COLOR A: 60990 (60990A)

BIARRITZ WHITE, BIARRITZ WHITE MET

BASE #	BASE NAME	1 QT Grams	1 QUART Cum. Grams	1 GAL Grams	1 GALLON Cum. Grams
HB002	HYDRO BASE	492.78	492.78	1971.1	1971.1
HB990	WHITE	673.38	1166.15	2693.5	4664.6
HB259	LOW STRENGTH BLACK	13.27	1179.43	53.1	4717.7
HB409	PHTHALO BLUE	12.08	1191.50	48.3	4766.0
HB670	YELLOW OXIDE	3.63	1195.13	14.5	4780.5
HB779	RED OXIDE	2.42	1197.55	9.7	4790.2

COLOR B: 41100

CHARCOAL PEARL

BASE #	BASE NAME	1 QT Grams	1 QUART Cum. Grams	1 GAL Grams	1 GALLON Cum. Grams
HB002	HYDRO BASE	604.95	604.95	2419.8	2419.8
HB203	DEEP BLACK	98.45	703.40	393.8	2813.6
HB120	FINE ALUMINUM	59.95	763.35	239.8	3053.4
HB99M	WHITE PEARL	34.28	797.63	137.1	3190.5
HB300	CARBAZOLE VIOLET	21.38	819.00	85.5	3276.0
HB444	BLUE	21.35	840.35	85.4	3361.4
HB471	PHTHALO BLUE	18.20	858.55	72.8	3434.2
HB770	RED OXIDE	4.25	862.80	17.0	3451.2
HB090	FLOP CONTROL	89.90	952.70	359.6	3810.8

COLOR C: 64147

SALSA RED PEARL, SALSA RED PEARL MET

BASE #	BASE NAME	1 QT Grams	1 QUART Cum. Grams	1 GAL Grams	1 GALLON Cum. Grams
HB002 Step 1	HYDRO BASE	577.65	577.65	2310.6	2310.6
HB990 Step 1	WHITE	423.13	1000.78	1692.5	4003.1
HB250 Step 1	BLACK	101.73	1102.50	406.9	4410.0
HB002 Step 2	HYDRO BASE	588.85	1691.35	2355.4	6765.4
HB861 Step 2	MAROON	131.95	1823.30	527.8	7293.2
HB88M Step 2	SUPER RUSSET PEARL	51.35	1874.65	205.4	7498.6
HB870 Step 2	MAGENTA	35.65	1910.30	142.6	7641.2
HB88L Step 2	RUSSET PEARL	23.08	1933.38	92.3	7733.5
HB250 Step 2	BLACK	17.78	1951.15	71.1	7804.6
HB999 Step 2	LOW STRENGTH WHITE	8.38	1959.53	33.5	7838.1
HB090 Step 2	FLOP CONTROL	93.23	2052.75	372.9	8211.0