






Dutch Star 2017

- SKIN: 575874A EGGSHELL
- A - 44429B LIGHT CHAMPAGNE MET.
- B - 64443 PEARL BLACK MET.
- C - 64147 SALSA RED PEARL

UNIT: 606198
 DEALER: Tom Lindstrom RV
 SPECIAL: 573

PLEASE ACKNOWLEDGE AND DATE THE FOLLOWING
 ORDER/PRINT FOR APPROVAL TO BUILD, AND FAX TO
 NEWMAR (AT 574-773-2895) AS SOON AS POSSIBLE

DATE: _____

SIGN: _____

Paint Code Formulas - BASF Diamont

SPECIAL FOR UNIT # 606198 - 2017 DUTCH STAR

SKIN: 575874 (575874A)	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			Grams	Cum.	Grams	Cum. Grams
EGGSHELL	UR50	UNIVERSAL MID TEMP REDUCER	79.03	79.03	316.1	316.1
	BC191	0	733.45	812.48	2933.8	3249.9
	BC209	BLACK TONER	27.08	839.55	108.3	3358.2
	BC605	YELLOW OXIDE	24.55	864.10	98.2	3456.4
	BC805	RED OXIDE	4.33	868.43	17.3	3473.7
	BC101	FLOP CONTROL	87.15	955.58	348.6	3822.3
COLOR A: 44429 (44429B)	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			Grams	Cum.	Grams	Cum. Grams
LIGHT CHAMPAGNE MET	UR50	UNIVERSAL MID TEMP REDUCER	83.70	83.70	334.8	334.8
	BC821	DARK MAROON	6.00	89.70	24.0	358.8
	BC101	FLOP CONTROL	103.85	193.55	415.4	774.2
	BC170	MEDIUM IRIDESCENT	174.03	367.58	696.1	1470.3
	BC194	HI HIDING WHITE	10.98	378.55	43.9	1514.2
	BC171	MEDIUM ALUMINUM	405.40	783.95	1621.6	3135.8
	BC800	RED GOLD	43.48	827.43	173.9	3309.7
	BC250	BLUE BLACK	46.68	874.10	186.7	3496.4
COLOR B: 64443	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			Grams	Cum.	Grams	Cum. Grams
PEARL BLACK, BLACK PEARL MET	UR50	UNIVERSAL MID TEMP REDUCER	80.35	80.35	321.4	321.4
	BC105	WHITE	7.30	87.65	29.2	350.6
	BC118	BLUE PEARL	32.48	120.13	129.9	480.5
	BC1190	CRYSTAL WHITE	36.13	156.25	144.5	625.0
	BC171	MEDIUM ALUMINUM	4.88	161.13	19.5	644.5
	BC200	BLACK	674.85	835.98	2699.4	3343.9
	BC410	GREEN BLUE	11.78	847.75	47.1	3391.0
	BC805	RED OXIDE	12.58	860.33	50.3	3441.3
	BC101	FLOP CONTROL	8.93	869.25	35.7	3477.0
COLOR C: 64147	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			Grams	Cum.	Grams	Cum. Grams
SALSA RED PEARL, SALSA RED PEARL MET	UR50	UNIVERSAL MID TEMP REDUCER	80.73	80.73	322.9	322.9
	BC101	FLOP CONTROL	49.55	130.28	198.2	521.1
	BC105	WHITE	44.38	174.65	177.5	698.6
	BC116	SUPER RUSSET PEARL	212.63	387.28	850.5	1549.1
	BC200	BLACK	46.78	434.05	187.1	1736.2
	BC805	RED OXIDE	41.58	475.63	166.3	1902.5
	BC821	DARK MAROON	410.08	885.70	1640.3	3542.8

Paint Code Formulas - BASF Onyx Waterborne

SPECIAL FOR UNIT # 606198 - 2017 DUTCH STAR

SKIN: 575874 (575874A)	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			Grams	Cum.	Grams	Cum. Grams
EGGSHELL	HB002	HYDRO BASE	492.50	492.50	1970.0	1970.0
	HB990	WHITE	504.30	996.80	2017.2	3987.2
	HB779	RED OXIDE	65.05	1061.85	260.2	4247.4
	HB259	LOW STRENGTH BLACK	54.13	1115.98	216.5	4463.9
	HB670	YELLOW OXIDE	21.73	1137.70	86.9	4550.8
COLOR A: 44429 (44429A)	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			Grams	Cum.	Grams	Cum. Grams
LIGHT CHAMPAGNE MET	HB002	HYDRO BASE	598.90	598.90	2395.6	2395.6
	HB130	FINE ALUMINUM	120.23	719.13	480.9	2876.5
	HB150	MEDIUM ALUMINUM	86.10	805.23	344.4	3220.9
	HB999	LOW STRENGTH WHITE	66.23	871.45	264.9	3485.8
	HB780	RED GOLD	29.78	901.23	119.1	3604.9
	HB200	BLUE BLACK	19.85	921.08	79.4	3684.3
	HB861	MAROON	6.67	927.75	26.7	3711.0
	HB090	FLOP CONTROL	47.45	975.20	189.8	3900.8
COLOR B: 64443	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			Grams	Cum.	Grams	Cum. Grams
PEARL BLACK, BLACK PEARL MET	HB002	HYDRO BASE	665.58	665.58	2662.3	2662.3
	HB203	DEEP BLACK	211.58	877.15	846.3	3508.6
	HB46L	BLUE PEARL	31.33	908.48	125.3	3633.9
	HB99L	CRYSTAL WHITE	19.55	928.03	78.2	3712.1
	HB670	YELLOW OXIDE	13.65	941.68	54.6	3766.7
	HB999	LOW STRENGTH WHITE	3.93	945.60	15.7	3782.4
	HB150	MEDIUM ALUMINUM	2.95	948.55	11.8	3794.2
	HB090	FLOP CONTROL	8.85	957.40	35.4	3829.6
COLOR C: 64147	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			Grams	Cum.	Grams	Cum. Grams
SALSA RED PEARL, SALSA RED PEARL MET	HB002 Step 1	HYDRO BASE	577.65	577.65	2310.6	2310.6
	HB990 Step 1	WHITE	423.13	1000.78	1692.5	4003.1
	HB250 Step 1	BLACK	101.73	1102.50	406.9	4410.0
	HB002 Step 2	HYDRO BASE	588.85	1691.35	2355.4	6765.4
	HB861 Step 2	MAROON	131.95	1823.30	527.8	7293.2
	HB88M Step 2	SUPER RUSSET PEARL	51.35	1874.65	205.4	7498.6
	HB870 Step 2	MAGENTA	35.65	1910.30	142.6	7641.2
	HB88L Step 2	RUSSET PEARL	23.08	1933.38	92.3	7733.5
	HB250 Step 2	BLACK	17.78	1951.15	71.1	7804.6
	HB999 Step 2	LOW STRENGTH WHITE	8.38	1959.53	33.5	7838.1
	HB090 Step 2	FLOP CONTROL	93.23	2052.75	372.9	8211.0