



Dutch Star 2017

SKIN: 64443 PEARL BLACK MET.
A - 60990A BIARRITZ WHITE MET.
B - 62431 SILVER SHADOW PEARL
C - 51424 SAPPHIRE MET.

UNIT: 606352
DEALER: North Trail RV
SPECIAL: 1150

PLEASE ACKNOWLEDGE AND DATE THE FOLLOWING ORDER/PRINT FOR APPROVAL TO BUILD, AND FAX TO NEWMAR (AT 574-773-2895) AS SOON AS POSSIBLE

DATE: _____

SIGN: _____

Paint Code Formulas - BASF *Diamont*

SPECIAL FOR UNIT # 606352 - 2017 DUTCH STAR

SKIN: 64443

PEARL BLACK, BLACK PEARL MET

BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
UR50	UNIVERSAL MID TEMP REDUCER	80.35	80.35	321.4	321.4
BC105	WHITE	7.30	87.65	29.2	350.6
BC118	BLUE PEARL	32.48	120.13	129.9	480.5
BC1190	CRYSTAL WHITE	36.13	156.25	144.5	625.0
BC171	MEDIUM ALUMINUM	4.88	161.13	19.5	644.5
BC200	BLACK	674.85	835.98	2699.4	3343.9
BC410	GREEN BLUE	11.78	847.75	47.1	3391.0
BC805	RED OXIDE	12.58	860.33	50.3	3441.3
BC101	FLOP CONTROL	8.93	869.25	35.7	3477.0

COLOR A: 60990 (60990A)

BIARRITZ WHITE, BIARRITZ WHITE MET

BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
UR50	UNIVERSAL MID TEMP REDUCER	84.10	84.10	336.4	336.4
D902	HI HIDING WHITE	937.73	1021.83	3750.9	4087.3
BC209	BLACK TONER	28.60	1050.43	114.4	4201.7
BC605	YELLOW OXIDE	13.55	1063.98	54.2	4255.9

COLOR B: 62431

SILVER SHADOW PEARL, SILVER SHADOW MET

BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
UR50	UNIVERSAL MID TEMP REDUCER	79.95	79.95	319.8	319.8
BC101	FLOP CONTROL	15.78	95.73	63.1	382.9
BC140	MEDIUM FINE IRIDESCENT	113.33	209.05	453.3	836.2
BC171	MEDIUM ALUMINUM	383.83	592.88	1535.3	2371.5
BC260	SATIN BLACK	77.30	670.18	309.2	2680.7
BC800	RED GOLD	10.58	680.75	42.3	2723.0
CB64L	YELLOW PEARL	50.05	730.80	200.2	2923.2
BC100	CLEAR	147.53	878.33	590.1	3513.3

COLOR C: 51424

SAPPHIRE MET

BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
UR50	UNIVERSAL MID TEMP REDUCER	78.60	78.60	314.4	314.4
BC101	FLOP CONTROL	12.95	91.55	51.8	366.2
BC105	WHITE	12.93	104.48	51.7	417.9
BC201	DEEP BLACK	96.75	201.23	387.0	804.9
BC300	CARBAZOLE VIOLET	124.38	325.60	497.5	1302.4
BC140	MEDIUM FINE IRIDESCENT	34.55	360.15	138.2	1440.6
BC171	MEDIUM ALUMINUM	34.58	394.73	138.3	1578.9
BC406	PHTHALO BLUE	400.85	795.58	1603.4	3182.3
BC250	BLUE BLACK	68.28	863.85	273.1	3455.4

Paint Code Formulas - BASF *Onyx Waterborne*

SPECIAL FOR UNIT # 606352 - 2017 DUTCH STAR

SKIN: 64443

PEARL BLACK, BLACK PEARL MET

BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
HB002	HYDRO BASE	665.58	665.58	2662.3	2662.3
HB203	DEEP BLACK	211.58	877.15	846.3	3508.6
HB46L	BLUE PEARL	31.33	908.48	125.3	3633.9
HB99L	CRYSTAL WHITE	19.55	928.03	78.2	3712.1
HB670	YELLOW OXIDE	13.65	941.68	54.6	3766.7
HB999	LOW STRENGTH WHITE	3.93	945.60	15.7	3782.4
HB150	MEDIUM ALUMINUM	2.95	948.55	11.8	3794.2
HB090	FLOP CONTROL	8.85	957.40	35.4	3829.6

COLOR A: 60990 (60990A)

BIARRITZ WHITE, BIARRITZ WHITE MET

BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
HB002	HYDRO BASE	492.78	492.78	1971.1	1971.1
HB990	WHITE	673.38	1166.15	2693.5	4664.6
HB259	LOW STRENGTH BLACK	13.27	1179.43	53.1	4717.7
HB409	PHTHALO BLUE	12.08	1191.50	48.3	4766.0
HB670	YELLOW OXIDE	3.63	1195.13	14.5	4780.5
HB779	RED OXIDE	2.42	1197.55	9.7	4790.2

COLOR B: 62431

SILVER SHADOW PEARL, SILVER SHADOW MET

BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
HB002	HYDRO BASE	634.20	634.20	2536.8	2536.8
HB64L	GOLD PEARL	94.57	728.78	378.3	2915.1
HB110	ULTRA FINE ALUMINUM	87.90	816.68	351.6	3266.7
HB120	FINE ALUMINUM	50.08	866.75	200.3	3467.0
HB260	SATIN BLACK	37.80	904.55	151.2	3618.2
HB150	MEDIUM ALUMINUM	14.45	919.00	57.8	3676.0
HB780	RED GOLD	5.60	924.60	22.4	3698.4
HB090	FLOP CONTROL	46.75	971.35	187.0	3885.4

COLOR C: 51424

SAPPHIRE MET

BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
HB002	HYDRO BASE	584.33	584.33	2337.3	2337.3
HB471	PHTHALO BLUE	312.68	897.00	1250.7	3588.0
HB300	CARBAZOLE VIOLET	32.45	929.45	129.8	3717.8
HB200	BLUE BLACK	28.47	957.93	113.9	3831.7
HB110	ULTRA FINE ALUMINUM	5.90	963.83	23.6	3855.3
HB120	FINE ALUMINUM	1.97	965.80	7.9	3863.2
HB999	LOW STRENGTH WHITE	2.03	967.83	8.1	3871.3