





Dutch Star 2017

SKIN: 85670A NEWMAR SLATE MET.
A - 60990A BIARRITZ WHITE MET.
B - 64443 PEARL BLACK MET.
C - 64147 SALSA RED PEARL

UNIT: 606611
DEALER: National Indoor RV
SPECIAL: 1627

PLEASE ACKNOWLEDGE AND DATE THE FOLLOWING ORDER/PRINT FOR APPROVAL TO BUILD, AND FAX TO NEWMAR (AT 574-773-2895) AS SOON AS POSSIBLE

DATE: _____

SIGN: _____

Paint Code Formulas - BASF *Diamont*

SPECIAL FOR UNIT # 606611 - 2017 DUTCH STAR

SKIN: 85670 (85670A)

SLATE MET

BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
UR50	UNIVERSAL MID TEMP REDUCER	79.13	79.13	316.5	316.5
BC171	MEDIUM ALUMINUM	413.85	492.98	1655.4	1971.9
BC201	DEEP BLACK	212.13	705.10	848.5	2820.4
BC105	WHITE	66.08	771.18	264.3	3084.7
BC140	MEDIUM FINE IRIDESCENT	26.95	798.13	107.8	3192.5
BC101	FLOP CONTROL	23.48	821.60	93.9	3286.4
BC406	PHTHALO BLUE	20.88	842.48	83.5	3369.9
BC880	VIOLET	13.05	855.53	52.2	3422.1
BC300	CARBAZOLE VIOLET	11.30	866.83	45.2	3467.3
BC510	YELLOW GREEN	2.60	869.43	10.4	3477.7

COLOR A: 60990 (60990A)

BIARRITZ WHITE, BIARRITZ WHITE MET

BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
UR50	UNIVERSAL MID TEMP REDUCER	84.10	84.10	336.4	336.4
D902	HI HIDING WHITE	937.73	1021.83	3750.9	4087.3
BC209	BLACK TONER	28.60	1050.43	114.4	4201.7
BC605	YELLOW OXIDE	13.55	1063.98	54.2	4255.9

COLOR B: 64443

PEARL BLACK, BLACK PEARL MET

BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
UR50	UNIVERSAL MID TEMP REDUCER	80.35	80.35	321.4	321.4
BC105	WHITE	7.30	87.65	29.2	350.6
BC118	BLUE PEARL	32.48	120.13	129.9	480.5
BC1190	CRYSTAL WHITE	36.13	156.25	144.5	625.0
BC171	MEDIUM ALUMINUM	4.88	161.13	19.5	644.5
BC200	BLACK	674.85	835.98	2699.4	3343.9
BC410	GREEN BLUE	11.78	847.75	47.1	3391.0
BC805	RED OXIDE	12.58	860.33	50.3	3441.3
BC101	FLOP CONTROL	8.93	869.25	35.7	3477.0

COLOR C: 64147

SALSA RED PEARL, SALSA RED PEARL MET

BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
UR50	UNIVERSAL MID TEMP REDUCER	80.73	80.73	322.9	322.9
BC101	FLOP CONTROL	49.55	130.28	198.2	521.1
BC105	WHITE	44.38	174.65	177.5	698.6
BC116	SUPER RUSSET PEARL	212.63	387.28	850.5	1549.1
BC200	BLACK	46.78	434.05	187.1	1736.2
BC805	RED OXIDE	41.58	475.63	166.3	1902.5
BC821	DARK MAROON	410.08	885.70	1640.3	3542.8

Paint Code Formulas - BASF *Onyx Waterborne*

SPECIAL FOR UNIT # 606611 - 2017 DUTCH STAR

SKIN: 85670

SLATE MET

BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
HB002	HYDRO BASE	652.05	652.05	2608.2	2608.2
HB203	DEEP BLACK	95.85	747.90	383.4	2991.6
HB130	FINE ALUMINUM	76.25	824.15	305.0	3296.6
HB140	MEDIUM ALUMINUM	55.65	879.80	222.6	3519.2
HB200	BLUE BLACK	49.45	929.25	197.8	3717.0
HB444	BLUE	16.53	945.78	66.1	3783.1
HB840	RED	15.45	961.23	61.8	3844.9

COLOR A: 60990 (60990A)

BIARRITZ WHITE, BIARRITZ WHITE MET

BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
HB002	HYDRO BASE	492.78	492.78	1971.1	1971.1
HB990	WHITE	673.38	1166.15	2693.5	4664.6
HB259	LOW STRENGTH BLACK	13.27	1179.43	53.1	4717.7
HB409	PHTHALO BLUE	12.08	1191.50	48.3	4766.0
HB670	YELLOW OXIDE	3.63	1195.13	14.5	4780.5
HB779	RED OXIDE	2.42	1197.55	9.7	4790.2

COLOR B: 64443

PEARL BLACK, BLACK PEARL MET

BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
HB002	HYDRO BASE	665.58	665.58	2662.3	2662.3
HB203	DEEP BLACK	211.58	877.15	846.3	3508.6
HB46L	BLUE PEARL	31.33	908.48	125.3	3633.9
HB99L	CRYSTAL WHITE	19.55	928.03	78.2	3712.1
HB670	YELLOW OXIDE	13.65	941.68	54.6	3766.7
HB999	LOW STRENGTH WHITE	3.93	945.60	15.7	3782.4
HB150	MEDIUM ALUMINUM	2.95	948.55	11.8	3794.2
HB090	FLOP CONTROL	8.85	957.40	35.4	3829.6

COLOR C: 64147

SALSA RED PEARL, SALSA RED PEARL MET

BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
HB002 Step 1	HYDRO BASE	577.65	577.65	2310.6	2310.6
HB990 Step 1	WHITE	423.13	1000.78	1692.5	4003.1
HB250 Step 1	BLACK	101.73	1102.50	406.9	4410.0
HB002 Step 2	HYDRO BASE	588.85	1691.35	2355.4	6765.4
HB861 Step 2	MAROON	131.95	1823.30	527.8	7293.2
HB88M Step 2	SUPER RUSSET PEARL	51.35	1874.65	205.4	7498.6
HB870 Step 2	MAGENTA	35.65	1910.30	142.6	7641.2
HB88L Step 2	RUSSET PEARL	23.08	1933.38	92.3	7733.5
HB250 Step 2	BLACK	17.78	1951.15	71.1	7804.6
HB999 Step 2	LOW STRENGTH WHITE	8.38	1959.53	33.5	7838.1
HB090 Step 2	FLOP CONTROL	93.23	2052.75	372.9	8211.0