






Dutch Star 2017

- SKIN: 670088 NEW NEWMAR SILVER
- A - 64443 PEARL BLACK MET.
- B - 60990A BIARRITZ WHITE MET.
- C - 64147 SALSA RED PEARL

UNIT: 606664

DEALER: Desert Autoplex

SPECIAL: 1831

PLEASE ACKNOWLEDGE AND DATE THE FOLLOWING
ORDER/PRINT FOR APPROVAL TO BUILD, AND FAX TO
NEWMAR (AT 574-773-2895) AS SOON AS POSSIBLE

DATE: _____

SIGN: _____

COLOR C: 64147

SKIN: 670088		BASE #	BASE NAME	1 QT Grams	1 QUART Cum. Grams	1 GAL Grams	1 GALLON Cum. Grams
NEW NEWMAR SILVER							
COLOR A: 64443		BASE #	BASE NAME	1 QT Grams	1 QUART Cum. Grams	1 GAL Grams	1 GALLON Cum. Grams
PEARL BLACK, BLACK PEARL MET	HB002	HYDRO BASE	665.58	665.58	2662.3	2662.3	
	HB203	DEEP BLACK	211.58	877.15	846.3	3508.6	
	HB46L	BLUE PEARL	31.33	908.48	125.3	3633.9	
	HB99L	CRYSTAL WHITE	19.55	928.03	78.2	3712.1	
	HB670	YELLOW OXIDE	13.65	941.68	54.6	3766.7	
	HB999	LOW STRENGTH WHITE	3.93	945.60	15.7	3782.4	
	HB150	MEDIUM ALUMINUM	2.95	948.55	11.8	3794.2	
	HB090	FLOP CONTROL	8.85	957.40	35.4	3829.6	
COLOR B: 60990 (60990A)		BASE #	BASE NAME	1 QT Grams	1 QUART Cum. Grams	1 GAL Grams	1 GALLON Cum. Grams
BIARRITZ WHITE, BIARRITZ WHITE MET	HB002	HYDRO BASE	492.78	492.78	1971.1	1971.1	
	HB990	WHITE	673.38	1166.15	2693.5	4664.6	
	HB259	LOW STRENGTH BLACK	13.27	1179.43	53.1	4717.7	
	HB409	PHTHALO BLUE	12.08	1191.50	48.3	4766.0	
	HB670	YELLOW OXIDE	3.63	1195.13	14.5	4780.5	
	HB779	RED OXIDE	2.42	1197.55	9.7	4790.2	
COLOR C: 64147		BASE #	BASE NAME	1 QT Grams	1 QUART Cum. Grams	1 GAL Grams	1 GALLON Cum. Grams
SALSA RED PEARL, SALSA RED PEARL MET	HB002 Step 1	HYDRO BASE	577.65	577.65	2310.6	2310.6	
	HB990 Step 1	WHITE	423.13	1000.78	1692.5	4003.1	
	HB250 Step 1	BLACK	101.73	1102.50	406.9	4410.0	
	HB002 Step 2	HYDRO BASE	588.85	1691.35	2355.4	6765.4	
	HB861 Step 2	MAROON	131.95	1823.30	527.8	7293.2	
	HB88M Step 2	SUPER RUSSET PEARL	51.35	1874.65	205.4	7498.6	
	HB870 Step 2	MAGENTA	35.65	1910.30	142.6	7641.2	
	HB88L Step 2	RUSSET PEARL	23.08	1933.38	92.3	7733.5	
	HB250 Step 2	BLACK	17.78	1951.15	71.1	7804.6	
	HB999 Step 2	LOW STRENGTH WHITE	8.38	1959.53	33.5	7838.1	
	HB090 Step 2	FLOP CONTROL	93.23	2052.75	372.9	8211.0	