



2017 Essex

SKIN: 62310 LABRADOR BLACK PEARL
A - 575874A EGGSHELL
B - 54697A GOLD FIREMIST MET.
C - 574482 ROSSO BORDEAU

UNIT: 801224
DEALER: North Trail RV
SPECIAL: 893 (REV. 1)

PLEASE ACKNOWLEDGE AND DATE THE FOLLOWING ORDER/PRINT FOR APPROVAL TO BUILD, AND FAX TO NEWMAR (AT 574-773-2895) AS SOON AS POSSIBLE

DATE: _____

SIGN: _____

Paint Code Formulas - BASF *Diamont*

SPECIAL FOR UNIT # 801224 - 2017 ESSEX

SKIN: 62310

LABRADOR BLACK PEARL, LABRADOR BLACK MET

BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
UR50	UNIVERSAL MID TEMP REDUCER	78.90	78.90	315.6	315.6
BC101	FLOP CONTROL	14.80	93.70	59.2	374.8
BC105	WHITE	21.73	115.43	86.9	461.7
BC200	BLACK	712.03	827.45	2848.1	3309.8
BC605	YELLOW OXIDE	13.00	840.45	52.0	3361.8
BC805	RED OXIDE	21.73	862.18	86.9	3448.7
CB34M	VIOLET PEARL	2.63	864.80	10.5	3459.2
CB44L	BRIGHT BLUE	2.63	867.43	10.5	3469.7

COLOR A: 575874 (575874A)

EGGSHELL

BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
UR50	UNIVERSAL MID TEMP REDUCER	79.03	79.03	316.1	316.1
BC191	0	733.45	812.48	2933.8	3249.9
BC209	BLACK TONER	27.08	839.55	108.3	3358.2
BC605	YELLOW OXIDE	24.55	864.10	98.2	3456.4
BC805	RED OXIDE	4.33	868.43	17.3	3473.7
BC101	FLOP CONTROL	87.15	955.58	348.6	3822.3

COLOR B: 54697 (54697A)

GOLD FIREMIST MET

BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
UR50	UNIVERSAL MID TEMP REDUCER	80.73	80.73	322.9	322.9
BC101	FLOP CONTROL	28.53	109.25	114.1	437.0
BC105	WHITE	33.73	142.98	134.9	571.9
BC171	MEDIUM ALUMINUM	55.83	198.80	223.3	795.2
BC180	COARSE IRIDESCENT	396.00	594.80	1584.0	2379.2
BC200	BLACK	81.93	676.73	327.7	2706.9
BC600	GOLD	40.18	716.90	160.7	2867.6
BC800	RED GOLD	34.55	751.45	138.2	3005.8
CB66V	GOLD ALUMINUM	45.38	796.83	181.5	3187.3
BC100	CLEAR	91.58	888.40	366.3	3553.6

COLOR C: 574482

ROSSO BORDEAU

BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
UR50	UNIVERSAL MID TEMP REDUCER	79.53	79.53	318.1	318.1
BC140	MEDIUM FINE IRIDESCENT	9.58	89.10	38.3	356.4
BC170	MEDIUM IRIDESCENT	14.33	103.43	57.3	413.7
BC300	CARBAZOLE VIOLET	104.13	207.55	416.5	830.2
BC116	SUPER RUSSET PEARL	38.13	245.68	152.5	982.7
BC200	BLACK	41.38	287.05	165.5	1148.2
BC805	RED OXIDE	58.88	345.93	235.5	1383.7
BC821	DARK MAROON	528.65	874.58	2114.6	3498.3

Paint Code Formulas - BASF *Onyx Waterborne*

SPECIAL FOR UNIT # 801224 - 2017 ESSEX

SKIN: 62310

LABRADOR BLACK PEARL, LABRADOR BLACK MET

BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
HB002	HYDRO BASE	652.38	652.38	2609.5	2609.5
HB203	DEEP BLACK	217.03	869.40	868.1	3477.6
HB200	BLUE BLACK	32.30	901.70	129.2	3606.8
HB670	YELLOW OXIDE	13.65	915.35	54.6	3661.4
HB999	LOW STRENGTH WHITE	11.70	927.05	46.8	3708.2
HB770	RED OXIDE	6.85	933.90	27.4	3735.6
HB46L	BLUE PEARL	2.88	936.78	11.5	3747.1
CB34M	VIOLET PEARL	2.95	939.73	11.8	3758.9
HB740	BRIGHT ORANGE	1.98	941.70	7.9	3766.8
HB090	FLOP CONTROL	12.70	954.40	50.8	3817.6

COLOR A: 575874 (575874A)

EGGSHELL

BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
HB002	HYDRO BASE	492.50	492.50	1970.0	1970.0
HB990	WHITE	504.30	996.80	2017.2	3987.2
HB779	RED OXIDE	65.05	1061.85	260.2	4247.4
HB259	LOW STRENGTH BLACK	54.13	1115.98	216.5	4463.9
HB670	YELLOW OXIDE	21.73	1137.70	86.9	4550.8

COLOR B: 54697 (54697A)

GOLD FIREMIST MET

BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams

COLOR C: 574482

ROSSO BORDEAU

BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
HB002 Step 1	HYDRO BASE	537.30	537.30	2149.2	2149.2
HB990 Step 1	WHITE	565.23	1102.53	2260.9	4410.1
HB250 Step 1	BLACK	53.63	1156.15	214.5	4624.6
HB002 Step 2	HYDRO BASE	622.75	1778.90	2491.0	7115.6
HB861 Step 2	MAROON	208.83	1987.73	835.3	7950.9
HB300 Step 2	CARBAZOLE VIOLET	46.35	2034.08	185.4	8136.3
HB88L Step 2	RUSSET PEARL	29.93	2064.00	119.7	8256.0
HB740 Step 2	BRIGHT ORANGE	18.38	2082.38	73.5	8329.5
HB200 Step 2	BLUE BLACK	13.55	2095.93	54.2	8383.7
HB961 Step 2	TRANSPARENT WHITE	7.68	2103.60	30.7	8414.4
HB130 Step 2	FINE ALUMINUM	1.92	2105.53	7.7	8422.1
HB090 Step 2	FLOP CONTROL	4.80	2110.33	19.2	8441.3