






2017 LONDONAIRE

17B510 WESTPORT

- SKIN: 85670A NEWMAR SLATE MET.
- A - 64443 PEARL BLACK MET.
- B - 64147 SALSA RED PEARL
- C - 60990A BIARRITZ WHITE MET.

AWNING: GIRARD G2000
FABRIC: CHARCOAL TWEED
HARDWARE: BLACK

2017 LONDON AIRE 17B510 - WESTPORT

[illegible]

Paint Code Formulas - BASF Onyx Waterborne

2017 LONDON AIRE 17B510 - WESTPORT

SKIN: 85670		BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
SLATE MET		HB002	HYDRO BASE	652.05	652.05	2608.2	2608.2
		HB203	DEEP BLACK	95.85	747.90	383.4	2991.6
		HB130	FINE ALUMINUM	76.25	824.15	305.0	3296.6
		HB140	MEDIUM ALUMINUM	55.65	879.80	222.6	3519.2
		HB200	BLUE BLACK	49.45	929.25	197.8	3717.0
		HB444	BLUE	16.53	945.78	66.1	3783.1
		HB840	RED	15.45	961.23	61.8	3844.9
COLOR A: 64443		BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
PEARL BLACK, BLACK PEARL MET		HB002	HYDRO BASE	665.58	665.58	2662.3	2662.3
		HB203	DEEP BLACK	211.58	877.15	846.3	3508.6
		HB46L	BLUE PEARL	31.33	908.48	125.3	3633.9
		HB99L	CRYSTAL WHITE	19.55	928.03	78.2	3712.1
		HB670	YELLOW OXIDE	13.65	941.68	54.6	3766.7
		HB999	LOW STRENGTH WHITE	3.93	945.60	15.7	3782.4
		HB150	MEDIUM ALUMINUM	2.95	948.55	11.8	3794.2
		HB090	FLOP CONTROL	8.85	957.40	35.4	3829.6
COLOR B: 64147		BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
SALSA RED PEARL, SALSA RED PEARL MET		HB002 Step 1	HYDRO BASE	577.65	577.65	2310.6	2310.6
		HB990 Step 1	WHITE	423.13	1000.78	1692.5	4003.1
		HB250 Step 1	BLACK	101.73	1102.50	406.9	4410.0
		HB002 Step 2	HYDRO BASE	588.85	1691.35	2355.4	6765.4
		HB861 Step 2	MAROON	131.95	1823.30	527.8	7293.2
		HB88M Step 2	SUPER RUSSET PEARL	51.35	1874.65	205.4	7498.6
		HB870 Step 2	MAGENTA	35.65	1910.30	142.6	7641.2
		HB88L Step 2	RUSSET PEARL	23.08	1933.38	92.3	7733.5
		HB250 Step 2	BLACK	17.78	1951.15	71.1	7804.6
		HB999 Step 2	LOW STRENGTH WHITE	8.38	1959.53	33.5	7838.1
		HB090 Step 2	FLOP CONTROL	93.23	2052.75	372.9	8211.0
COLOR C: 60990 (60990A)		BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
BIARRITZ WHITE, BIARRITZ WHITE MET		HB002	HYDRO BASE	492.78	492.78	1971.1	1971.1
		HB990	WHITE	673.38	1166.15	2693.5	4664.6
		HB259	LOW STRENGTH BLACK	13.27	1179.43	53.1	4717.7
		HB409	PHTHALO BLUE	12.08	1191.50	48.3	4766.0
		HB670	YELLOW OXIDE	3.63	1195.13	14.5	4780.5
		HB779	RED OXIDE	2.42	1197.55	9.7	4790.2