



2018

KING AIRE

- SKIN: 62922A GALAXY GOLD MET.
- A - 56680 CAJUN SPICE OBSIDIAN
- B - 574482 ROSSO BORDEAU
- C - 60990A BIARRITZ WHITE MET.
- D - BC201 BLACK TONER

UNIT: 530433

DEALER: National Indoor RV

SPECIAL: 253

PLEASE ACKNOWLEDGE AND DATE THE FOLLOWING ORDER/PRINT FOR APPROVAL TO BUILD, AND FAX TO NEWMAR (AT 574-773-2895) AS SOON AS POSSIBLE

DATE: _____

SIGN: _____

Paint Code Formulas - BASF Onyx Waterborne

SPECIAL FOR UNIT # 530433 - 2018 KING AIRE

SKIN: 62922 (62922A)	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
GALAXY GOLD MET	HB002	HYDRO BASE	631.38	631.38	2525.5	2525.5
	HB120	FINE ALUMINUM	146.75	778.13	587.0	3112.5
	CB85L	RED PEARL	107.60	885.73	430.4	3542.9
	HB670	YELLOW OXIDE	31.53	917.25	126.1	3669.0
	HB617	ORGANIC YELLOW	20.73	937.98	82.9	3751.9
	HB770	RED OXIDE	13.07	951.05	52.3	3804.2
	HB259	LOW STRENGTH BLACK	13.00	964.05	52.0	3856.2
	HB740	BRIGHT ORANGE	5.45	969.50	21.8	3878.0
	HB090	FLOP CONTROL	29.33	998.83	117.3	3995.3
COLOR A: 56680	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
CAJON SPICE OBSIDIAN PEARL, OBSIDIAN BLACK MET	HB002	HYDRO BASE	665.33	665.33	2661.3	2661.3
	HB203	DEEP BLACK	227.93	893.25	911.7	3573.0
	HB200	BLUE BLACK	20.25	913.50	81.0	3654.0
	HB770	RED OXIDE	11.63	925.13	46.5	3700.5
	HB670	YELLOW OXIDE	9.70	934.83	38.8	3739.3
	HB999	LOW STRENGTH WHITE	8.67	943.50	34.7	3774.0
	HB462	SAPPHIRE 2	5.85	949.35	23.4	3797.4
	HB150	MEDIUM ALUMINUM	2.00	951.35	8.0	3805.4
	HB130	FINE ALUMINUM	1.92	953.28	7.7	3813.1
COLOR B: 574482	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
ROSSO BORDEAU	HB002 Step 1	HYDRO BASE	537.30	537.30	2149.2	2149.2
	HB990 Step 1	WHITE	565.23	1102.53	2260.9	4410.1
	HB250 Step 1	BLACK	53.63	1156.15	214.5	4624.6
	HB002 Step 2	HYDRO BASE	622.75	1778.90	2491.0	7115.6
	HB861 Step 2	MAROON	208.83	1987.73	835.3	7950.9
	HB300 Step 2	CARBAZOLE VIOLET	46.35	2034.08	185.4	8136.3
	HB88L Step 2	RUSSET PEARL	29.93	2064.00	119.7	8256.0
	HB740 Step 2	BRIGHT ORANGE	18.38	2082.38	73.5	8329.5
	HB200 Step 2	BLUE BLACK	13.55	2095.93	54.2	8383.7
	HB961 Step 2	TRANSPARENT WHITE	7.68	2103.60	30.7	8414.4
	HB130 Step 2	FINE ALUMINUM	1.92	2105.53	7.7	8422.1
	HB090 Step 2	FLOP CONTROL	4.80	2110.33	19.2	8441.3
	COLOR C: 60990 (60990A)	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams
BIARRITZ WHITE, BIARRITZ WHITE MET	HB002	HYDRO BASE	492.78	492.78	1971.1	1971.1
	HB990	WHITE	673.38	1166.15	2693.5	4664.6
	HB259	LOW STRENGTH BLACK	13.27	1179.43	53.1	4717.7
	HB409	PHTHALO BLUE	12.08	1191.50	48.3	4766.0
	HB670	YELLOW OXIDE	3.63	1195.13	14.5	4780.5
	HB779	RED OXIDE	2.42	1197.55	9.7	4790.2

