






Dutch Star 2018

- SKIN: 62431 SILVER SHADOW PEARL
- A - 64443 PEARL BLACK MET.
- B - 60427 PASSION RED MICA
- C - 60990A BIARRITZ WHITE MET.

UNIT: 607158

DEALER: Holland Motor Homes

SPECIAL: 1372

**PLEASE ACKNOWLEDGE AND DATE THE FOLLOWING
ORDER/PRINT FOR APPROVAL TO BUILD, AND FAX TO
NEWMAR (AT 574-773-2895) AS SOON AS POSSIBLE**

DATE: _____

SIGN: _____

Paint Code Formulas - BASF Onyx Waterborne

SPECIAL FOR UNIT 607158 - 2018 DUTCH STAR

SKIN: 62431 SILVER SHADOW PEARL, SILVER SHADOW MET	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			<i>Grams</i>	<i>Cum.</i>	<i>Grams</i>	<i>Cum. Grams</i>
	HB002	HYDRO BASE	634.20	634.20	2536.8	2536.8
	HB64L	GOLD PEARL	94.57	728.78	378.3	2915.1
	HB110	ULTRA FINE ALUMINUM	87.90	816.68	351.6	3266.7
	HB120	FINE ALUMINUM	50.08	866.75	200.3	3467.0
	HB260	SATIN BLACK	37.80	904.55	151.2	3618.2
	HB150	MEDIUM ALUMINUM	14.45	919.00	57.8	3676.0
	HB780	RED GOLD	5.60	924.60	22.4	3698.4
	HB090	FLOP CONTROL	46.75	971.35	187.0	3885.4
COLOR A: 64443 PEARL BLACK, BLACK PEARL MET	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			<i>Grams</i>	<i>Cum.</i>	<i>Grams</i>	<i>Cum. Grams</i>
	HB002	HYDRO BASE	665.58	665.58	2662.3	2662.3
	HB203	DEEP BLACK	211.58	877.15	846.3	3508.6
	HB46L	BLUE PEARL	31.33	908.48	125.3	3633.9
	HB99L	CRYSTAL WHITE	19.55	928.03	78.2	3712.1
	HB670	YELLOW OXIDE	13.65	941.68	54.6	3766.7
	HB999	LOW STRENGTH WHITE	3.93	945.60	15.7	3782.4
	HB150	MEDIUM ALUMINUM	2.95	948.55	11.8	3794.2
	HB090	FLOP CONTROL	8.85	957.40	35.4	3829.6
COLOR B: 60427 PASSION RED MICA, PASSION RED MICA MET	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			<i>Grams</i>	<i>Cum.</i>	<i>Grams</i>	<i>Cum. Grams</i>
	HB002 Step 1	HYDRO BASE	577.65	577.65	2310.6	2310.6
	HB990 Step 1	WHITE	423.13	1000.78	1692.5	4003.1
	HB250 Step 1	BLACK	101.73	1102.50	406.9	4410.0
	HB002 Step 2	HYDRO BASE	608.55	1711.05	2434.2	6844.2
	HB88M Step 2	SUPER RUSSET PEARL	123.83	1834.88	495.3	7339.5
	HB861 Step 2	MAROON	86.05	1920.93	344.2	7683.7
	HB840 Step 2	RED	77.65	1998.58	310.6	7994.3
	HB999 Step 2	LOW STRENGTH WHITE	6.25	2004.83	25.0	8019.3
COLOR C: 60990 (60990A) BIARRITZ WHITE, BIARRITZ WHITE MET	BASE #	BASE NAME	1 QT	1 QUART	1 GLN	1 GALLON
			<i>Grams</i>	<i>Cum.</i>	<i>Grams</i>	<i>Cum. Grams</i>
	HB002	HYDRO BASE	492.78	492.78	1971.1	1971.1
	HB990	WHITE	673.38	1166.15	2693.5	4664.6
	HB259	LOW STRENGTH BLACK	13.27	1179.43	53.1	4717.7
	HB409	PHTHALO BLUE	12.08	1191.50	48.3	4766.0
	HB670	YELLOW OXIDE	3.63	1195.13	14.5	4780.5
	HB779	RED OXIDE	2.42	1197.55	9.7	4790.2