




2019

VENTANA

- SKIN: 65594 NEWMAR DESERT GOLD
- A - 60990A BIARRITZ WHITE MET.
- B - 56680B CAJUN SPICE OBSIDIAN
- C - 574482 ROSSO BORDEAU
- D - 65594 NEWMAR DESERT GOLD

UNIT: 414101



DEALER: Mount Comfort RV

SPECIAL: 690

**PLEASE ACKNOWLEDGE AND DATE THE FOLLOWING
ORDER/PRINT FOR APPROVAL TO BUILD, AND FAX TO
NEWMAR (AT 574-773-2895) AS SOON AS POSSIBLE**

DATE: _____

SIGN: _____



COLOR C: 574482	BASE #	BASE NAME	1 QT	1 QUART	1 GAL	1 GALLON
			Grams	Cum. Grams	Grams	Cum. Grams
ROSSO BORDEAU	UR50	UNIVERSAL MID TEMP REDUCER	79.53	79.53	318.1	318.1
	BC140	MEDIUM FINE IRIDESCENT	9.58	89.10	38.3	356.4
	BC170	MEDIUM IRIDESCENT	14.33	103.43	57.3	413.7
	BC300	CARBAZOLE VIOLET	104.13	207.55	416.5	830.2
	BC116	SUPER RUSSET PEARL	38.13	245.68	152.5	982.7
	BC200	BLACK	41.38	287.05	165.5	1148.2
	BC805	RED OXIDE	58.88	345.93	235.5	1383.7
	BC821	DARK MAROON	528.65	874.58	2114.6	3498.3

Paint Code Formulas - BASF *Diamont*

SPECIAL FOR UNIT 414101 - 2019 VENTANA

COLOR D: 65594	BASE #	BASE NAME	1 QT	1 QUART	1 GAL	1 GALLON
			<i>Grams</i>	<i>Cum. Grams</i>	<i>Grams</i>	<i>Cum. Grams</i>
DESSERT GOLD MET	UR50	UNIVERSAL MID TEMP REDUCER	80.78	80.78	323.1	323.1
	BC101	FLOP CONTROL	66.73	147.50	266.9	590.0
	BC105	WHITE	69.40	216.90	277.6	867.6
	BC110	WHITE PEARL	184.43	401.33	737.7	1605.3
	BC171	MEDIUM ALUMINUM	377.63	778.95	1510.5	3115.8
	BC201	DEEP BLACK	18.45	797.40	73.8	3189.6
	BC600	GOLD	28.10	825.50	112.4	3302.0
	BC605	YELLOW OXIDE	20.15	845.65	80.6	3382.6
	BC800	RED GOLD	29.83	875.48	119.3	3501.9
	BC821	DARK MAROON	2.65	878.13	10.6	3512.5

Paint Code Formulas - BASF Onyx Waterborne

SPECIAL FOR UNIT 414101 - 2019 VENTANA

SKIN: 65594	BASE #	BASE NAME	1 QT	1 QUART	1 GAL	1 GALLON
			Grams	Cum. Grams	Grams	Cum. Grams
DESSERT GOLD MET, DESSERT GOLD	HB002	HYDRO BASE	587.33	587.33	2349.3	2349.3
	HB99M	WHITE PEARL	189.28	776.60	757.1	3106.4
	HB120	FINE ALUMINUM	79.00	855.60	316.0	3422.4
	HB680	GOLD	19.20	874.80	76.8	3499.2
	HB780	RED GOLD	15.60	890.40	62.4	3561.6
	HB999	LOW STRENGTH WHITE	14.33	904.73	57.3	3618.9
	HB670	YELLOW OXIDE	8.40	913.13	33.6	3652.5
	HB203	DEEP BLACK	7.20	920.33	28.8	3681.3
	HB090	FLOP CONTROL	61.10	981.43	244.4	3925.7
COLOR A: 60990 (60990A)	BASE #	BASE NAME	1 QT	1 QUART	1 GAL	1 GALLON
			Grams	Cum. Grams	Grams	Cum. Grams
BIARRITZ WHITE, BIARRITZ WHITE MET	HB002	HYDRO BASE	492.78	492.78	1971.1	1971.1
	HB990	WHITE	673.38	1166.15	2693.5	4664.6
	HB259	LOW STRENGTH BLACK	13.27	1179.43	53.1	4717.7
	HB409	PHTHALO BLUE	12.08	1191.50	48.3	4766.0
	HB670	YELLOW OXIDE	3.63	1195.13	14.5	4780.5
	HB779	RED OXIDE	2.42	1197.55	9.7	4790.2
COLOR B: 56680	BASE #	BASE NAME	1 QT	1 QUART	1 GAL	1 GALLON
			Grams	Cum. Grams	Grams	Cum. Grams
CAJON SPICE OBSIDIAN PEARL, OBSIDIAN BLACK MET	HB002	HYDRO BASE	665.33	665.33	2661.3	2661.3
	HB203	DEEP BLACK	227.93	893.25	911.7	3573.0
	HB200	BLUE BLACK	20.25	913.50	81.0	3654.0
	HB770	RED OXIDE	11.63	925.13	46.5	3700.5
	HB670	YELLOW OXIDE	9.70	934.83	38.8	3739.3
	HB999	LOW STRENGTH WHITE	8.67	943.50	34.7	3774.0
	HB462	SAPPHIRE 2	5.85	949.35	23.4	3797.4
	HB150	MEDIUM ALUMINUM	2.00	951.35	8.0	3805.4
	HB130	FINE ALUMINUM	1.92	953.28	7.7	3813.1
COLOR C: 574482	BASE #	BASE NAME	1 QT	1 QUART	1 GAL	1 GALLON
			Grams	Cum. Grams	Grams	Cum. Grams
ROSSO BORDEAU	HB002 Step 1	HYDRO BASE	537.30	537.30	2149.2	2149.2
	HB990 Step 1	WHITE	565.23	1102.53	2260.9	4410.1
	HB250 Step 1	BLACK	53.63	1156.15	214.5	4624.6
	HB002 Step 2	HYDRO BASE	622.75	1778.90	2491.0	7115.6
	HB861 Step 2	MAROON	208.83	1987.73	835.3	7950.9
	HB300 Step 2	CARBAZOLE VIOLET	46.35	2034.08	185.4	8136.3
	HB88L Step 2	RUSSET PEARL	29.93	2064.00	119.7	8256.0
	HB740 Step 2	BRIGHT ORANGE	18.38	2082.38	73.5	8329.5
	HB200 Step 2	BLUE BLACK	13.55	2095.93	54.2	8383.7
	HB961 Step 2	TRANSPARENT WHITE	7.68	2103.60	30.7	8414.4
	HB130 Step 2	FINE ALUMINUM	1.92	2105.53	7.7	8422.1
	HB090 Step 2	FLOP CONTROL	4.80	2110.33	19.2	8441.3

Paint Code Formulas - BASF Onyx Waterborne

SPECIAL FOR UNIT 414101 - 2019 VENTANA

COLOR D: 65594	BASE #	BASE NAME	1 QT	1 QUART	1 GAL	1 GALLON
			Grams	Cum. Grams	Grams	Cum. Grams
DESSERT GOLD MET, DESSERT GOLD	HB002	HYDRO BASE	587.33	587.33	2349.3	2349.3
	HB99M	WHITE PEARL	189.28	776.60	757.1	3106.4
	HB120	FINE ALUMINUM	79.00	855.60	316.0	3422.4
	HB680	GOLD	19.20	874.80	76.8	3499.2
	HB780	RED GOLD	15.60	890.40	62.4	3561.6
	HB999	LOW STRENGTH WHITE	14.33	904.73	57.3	3618.9
	HB670	YELLOW OXIDE	8.40	913.13	33.6	3652.5
	HB203	DEEP BLACK	7.20	920.33	28.8	3681.3
	HB090	FLOP CONTROL	61.10	981.43	244.4	3925.7