




Dutch Star 2019

- SKIN: 50288 DARK CARMEL MET.
- A - 44429B LIGHT CHAMPAGNE MET.
- B - 62447 NEWMAR BROWN MICA
- C - 575874A EGGSHELL

UNIT: 608334



DEALER: Independence RV

SPECIAL: 2251

PLEASE ACKNOWLEDGE AND DATE THE FOLLOWING
ORDER/PRINT FOR APPROVAL TO BUILD, AND FAX TO
NEWMAR (AT 574-773-2895) AS SOON AS POSSIBLE

DATE: _____

SIGN: _____



[illegible]

Paint Code Formulas - BASF Onyx Waterborne

SPECIAL FOR UNIT 608334 - 2019 DUTCH STAR

SKIN: 50288 DARK CARMEL MET, BLACK GOLD PEARL	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
	HB002	HYDRO BASE	609.23	609.23	2436.9	2436.9
	HB203	DEEP BLACK	178.05	787.28	712.2	3149.1
	HB780	RED GOLD	67.35	854.63	269.4	3418.5
	HB64L	GOLD PEARL	24.88	879.50	99.5	3518.0
	HB200	BLUE BLACK	8.23	887.73	32.9	3550.9
	HB090	FLOP CONTROL	68.28	956.00	273.1	3824.0
COLOR A: 44429 (44429A) LIGHT CHAMPAGNE MET	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
	HB002	HYDRO BASE	598.90	598.90	2395.6	2395.6
	HB130	FINE ALUMINUM	120.23	719.13	480.9	2876.5
	HB150	MEDIUM ALUMINUM	86.10	805.23	344.4	3220.9
	HB999	LOW STRENGTH WHITE	66.23	871.45	264.9	3485.8
	HB780	RED GOLD	29.78	901.23	119.1	3604.9
	HB200	BLUE BLACK	19.85	921.08	79.4	3684.3
	HB861	MAROON	6.67	927.75	26.7	3711.0
	HB090	FLOP CONTROL	47.45	975.20	189.8	3900.8
COLOR B: 62447 BROWN MICA, BROWN MICA MET	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
	HB002	HYDRO BASE	614.10	614.10	2456.4	2456.4
	HB203	DEEP BLACK	117.85	731.95	471.4	2927.8
	HB150	MEDIUM ALUMINUM	69.75	801.70	279.0	3206.8
	HB110	ULTRA FINE ALUMINUM	26.40	828.10	105.6	3312.4
	HB780	RED GOLD	21.65	849.75	86.6	3399.0
	HB880	RED VIOLET	13.25	863.00	53.0	3452.0
	HB861	MAROON	10.85	873.85	43.4	3495.4
	HB090	FLOP CONTROL	80.53	954.38	322.1	3817.5
COLOR C: 575874 (575874A) EGGSHELL	BASE #	BASE NAME	1 QT Grams	1 QUART Cum.	1 GLN Grams	1 GALLON Cum. Grams
	HB002	HYDRO BASE	492.50	492.50	1970.0	1970.0
	HB990	WHITE	504.30	996.80	2017.2	3987.2
	HB779	RED OXIDE	65.05	1061.85	260.2	4247.4
	HB259	LOW STRENGTH BLACK	54.13	1115.98	216.5	4463.9
	HB670	YELLOW OXIDE	21.73	1137.70	86.9	4550.8