



2008 TPFW
 Onyx 8B761
 SKIN: 44429 ANTELOPE METALLIC
 A. 62930 EXPRESSO METALLIC
 B. 57714 WARM GREY METALLIC
 C. 54690 PEWTER METALLIC

Unit: 310314
 Dealer: Midtown RV
 Special: 4549

PLEASE ACKNOWLEDGE AND DATE THE FOLLOWING
 ORDER/PRINT FOR APPROVAL TO BUILD, AND FAX TO
 NEWMAR (AT 574-773-2895) AS SOON AS POSSIBLE

DATE: _____

SIGN: _____

QUART

GALLON

SKIN:

FM 44429		0-0	LIGHT CHAMPAGNE MET	
Diamont	Using:	Standard	Step:	1/1
Base	Description	Amount	Cum.	
UR50	UNIVERSAL MID TEM...	83.2	83.2	
BC151	FINE ALUMINUM	576.1	659.3	
BC101	FLOP CONTROL	103.2	762.5	
BC250	BLUE BLACK	46.4	808.9	
BC800	RED GOLD	43.2	852.1	
BC190	WHITE	18.8	870.9	
BC821	DARK MAROON	6.0	876.9	

FM 44429		0-0	LIGHT CHAMPAGNE MET	
Diamont	Using:	Standard	Step:	1/1
Base	Description	Amount	Cum.	
UR50	UNIVERSAL MID TEM...	332.9	332.9	
BC151	FINE ALUMINUM	2304.4	2637.3	
BC101	FLOP CONTROL	413.0	3050.3	
BC250	BLUE BLACK	185.5	3235.8	
BC800	RED GOLD	172.9	3408.7	
BC190	WHITE	75.2	3483.9	
BC821	DARK MAROON	23.9	3507.8	

COLOR A:

FM 62930		0-0	ONYX MET	
Diamont	Using:	Standard	Step:	1/1
Base	Description	Amount	Cum.	
UR50	UNIVERSAL MID TEM...	78.8	78.8	
BC200	BLACK	645.1	723.9	
BC600	GOLD	47.6	771.5	
BC105	WHITE	40.8	812.3	
BC805	RED OXIDE	33.0	845.3	
BC140	MEDIUM FINE IRIDES...	11.2	856.5	
BC101	FLOP CONTROL	8.6	865.1	
BC171	MEDIUM ALUMINUM	1.8	866.9	

FM 62930		0-0	ONYX MET	
Diamont	Using:	Standard	Step:	1/1
Base	Description	Amount	Cum.	
UR50	UNIVERSAL MID TEM...	315.3	315.3	
BC200	BLACK	2580.5	2895.8	
BC600	GOLD	190.5	3086.3	
BC105	WHITE	163.2	3249.5	
BC805	RED OXIDE	131.9	3381.4	
BC140	MEDIUM FINE IRIDES...	44.8	3426.2	
BC101	FLOP CONTROL	34.4	3460.6	
BC171	MEDIUM ALUMINUM	7.3	3467.9	

COLOR B:

FM 57714		0-0	DARK FAWN MET	
Glasurit-90	Using:	Standard	Step:	1/1
Base	Description	Amount	Cum.	
M4	MIXING BASE	666.9	666.9	
M99/00	Super Fine Aluminum	22.1	689.0	
M99/07	Extra Coarse Silver	13.4	702.4	
A924	Waterborne Factor...	155.5	857.9	
A032	White	39.4	897.3	
A347	MAROON	8.6	905.9	
A306	Red Iron Oxide	5.7	911.6	
A148	Lemon Gold	3.8	915.4	
M1	EFFECT ADDITIVE	44.1	959.5	

FM 57714		0-0	DARK FAWN MET	
Glasurit-90	Using:	Standard	Step:	1/1
Base	Description	Amount	Cum.	
M4	MIXING BASE	2667.5	2667.5	
M99/00	Super Fine Aluminum	88.2	2755.7	
M99/07	Extra Coarse Silver	53.6	2809.3	
A924	Waterborne Factor...	621.9	3431.2	
A032	White	157.5	3588.7	
A347	MAROON	34.5	3623.2	
A306	Red Iron Oxide	23.0	3646.2	
A148	Lemon Gold	15.2	3661.4	
M1	EFFECT ADDITIVE	176.5	3837.9	

COLOR C:

FM 54690		0-0	PEWTER MET	
Diamont	Using:	Standard	Step:	1/1
Base	Description	Amount	Cum.	
UR50	UNIVERSAL MID TEM...	79.6	79.6	
BC171	MEDIUM ALUMINUM	335.5	415.1	
BC180	COARSE IRIDESCENT	235.5	650.6	
BC101	FLOP CONTROL	92.8	743.4	
BC200	BLACK	78.0	821.4	
BC250	BLUE BLACK	37.6	859.0	
BC800	RED GOLD	16.8	875.8	

FM 54690		0-0	PEWTER MET	
Diamont	Using:	Standard	Step:	1/1
Base	Description	Amount	Cum.	
UR50	UNIVERSAL MID TEM...	318.3	318.3	
BC171	MEDIUM ALUMINUM	1342.0	1660.3	
BC180	COARSE IRIDESCENT	942.1	2602.4	
BC101	FLOP CONTROL	371.0	2973.4	
BC200	BLACK	312.1	3285.5	
BC250	BLUE BLACK	150.5	3436.0	
BC800	RED GOLD	67.3	3503.3	